

Starflam® RF0097P

Ascend Performance Materials Operations LLC - *Polyamide 66/6 Copolymer*

General Information

Product Description

Starflam RF0097P is a glass fiber reinforced, flame retardant PA66/6 for injection molded applications. The material is halogen free and red phosphorus free.

General

Material Status	• Commercial: Active
Availability	• Europe • North America
Filler / Reinforcement	• Glass Fiber, 45% Filler by Weight
Additive	• Flame Retardant • Heat Stabilizer • Mold Release
Features	• Flame Retardant • Halogen Free • Heat Stabilized
Appearance	• Natural Color
Forms	• Pellets
Processing Method	• Injection Molding
Resin ID	• PA66/6-GF45 FR

Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density	1.59	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 73°F, 0.0787 in	0.60	--	%	
Flow : 73°F, 0.0787 in	0.40	--	%	
Water Absorption (24 hr, 73°F)	1.0	--	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	1.2	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (73°F)	2.29E+6	1.58E+6	psi	ISO 527-1
Tensile Stress (Break, 73°F)	24900	17000	psi	ISO 527-2
Tensile Strain (Break, 73°F)	2.2	3.3	%	ISO 527-2
Flexural Modulus (73°F)	2.42E+6	1.65E+6	psi	ISO 178
Flexural Stress (73°F)	40600	27800	psi	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-40°F	6.7	6.2	ft·lb/in ²	
-22°F	6.7	6.2	ft·lb/in ²	
73°F	6.2	6.7	ft·lb/in ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-40°F	30	30	ft·lb/in ²	
-22°F	32	32	ft·lb/in ²	
73°F	32	37	ft·lb/in ²	
Notched Izod Impact Strength				ISO 180/1A
-40°F	5.7	6.2	ft·lb/in ²	
-22°F	5.7	6.2	ft·lb/in ²	
73°F	6.2	6.7	ft·lb/in ²	
Unnotched Izod Impact Strength (73°F)	24	--	ft·lb/in ²	ISO 180/1U
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	491	487	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	469	453	°F	ISO 75-2/A
RTI Elec				UL 746B
0.031 in	302	--	°F	



0.06 in	302	--	°F	
0.12 in	302	--	°F	
RTI Imp				UL 746B
0.031 in	230	--	°F	
0.06 in	230	--	°F	
0.12 in	230	--	°F	
RTI Str				UL 746B
0.031 in	302	--	°F	
0.06 in	302	--	°F	
0.12 in	302	--	°F	
Electrical	Dry	Conditioned	Unit	Test Method
Electric Strength (0.0394 in)	740	710	V/mil	IEC 60243-1
Comparative Tracking Index (0.118 in)	600	--	V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746A
0.03 in	PLC 0	--		
0.06 in	PLC 0	--		
0.12 in	PLC 0	--		
Hot-wire Ignition (HWI)				UL 746A
0.03 in	PLC 0	--		
0.06 in	PLC 0	--		
0.12 in	PLC 0	--		
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.031 in	V-0	--		
0.06 in	V-0	--		
0.12 in	V-0	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.031 in	1760	--	°F	
0.06 in	1760	--	°F	
0.12 in	1760	--	°F	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.031 in	1470	--	°F	
0.06 in	1520	--	°F	
0.12 in	1520	--	°F	

Processing Information

Injection	Dry	Unit
Drying Temperature	176	°F
Drying Time	4.0	hr
Suggested Max Moisture	0.20	%
Rear Temperature	509 to 527	°F
Middle Temperature	509 to 527	°F
Front Temperature	518 to 536	°F
Processing (Melt) Temp	518 to 536	°F
Mold Temperature	140 to 212	°F

