

**TAIRILAC® AG16A1**

Formosa Chemicals &amp; Fibre Corporation - Acrylonitrile Butadiene Styrene

**General Information**
**Product Description**

Health Care Grade

Features: High rigid, Medium impact

**General**

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Features	• High Rigidity • Medium Impact Resistance
Uses	• Medical/Healthcare Applications
Agency Ratings	• EC 1907/2006 (REACH)
RoHS Compliance	• RoHS Compliant
UL File Number	• E162823

**Properties <sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity <sup>2</sup>	1.04		ASTM D792
Density (73°F)	1.04	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR)			ASTM D1238
200°C/5.0 kg	1.0	g/10 min	
220°C/10.0 kg	11	g/10 min	
Melt Mass-Flow Rate (MFR)			ISO 1133
200°C/5.0 kg	1.0	g/10 min	
220°C/10.0 kg	11	g/10 min	
Molding Shrinkage - Flow (0.126 in)	4.0E-3 to 7.0E-3	in/in	ASTM D955
Molding Shrinkage (0.126 in)	0.40 to 0.70	%	ISO 2577
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>3</sup> (73°F)	7250	psi	ASTM D638
Tensile Stress (73°F)	6820	psi	ISO 527-2/50
Flexural Modulus <sup>4</sup> (73°F)	370000	psi	ASTM D790
Flexural Modulus <sup>5</sup> (73°F)	334000	psi	ISO 178
Flexural Strength <sup>4</sup> (73°F)	12500	psi	ASTM D790
Flexural Stress <sup>5</sup> (73°F)	10400	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F, 0.157 in)	16	ft·lb/in <sup>2</sup>	ISO 179
Notched Izod Impact (73°F, 0.250 in)	5.1	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 73°F)	111		ASTM D785
Rockwell Hardness (R-Scale, 73°F)	111		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load <sup>6</sup> (264 psi, Unannealed, 0.250 in)	190	°F	ASTM D648
Deflection Temperature Under Load <sup>6</sup> (264 psi, Annealed, 0.250 in)	201	°F	ASTM D648
Deflection Temperature Under Load <sup>6</sup> (264 psi, Annealed, 0.157 in)	190	°F	ISO 75-2/A
Vicat Softening Temperature	201	°F	ASTM D1525 <sup>7</sup>
Vicat Softening Temperature	201	°F	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method



Flame Rating (0.06 to 0.12 in)	HB	UL 94
--------------------------------	----	-------

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature	158 to 176	°F
Drying Time	2.0 to 3.0	hr
Mold Temperature	104 to 176	°F
Injection Pressure	9960 to 15600	psi

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 23°C

<sup>3</sup> 2.0 in/min

<sup>4</sup> 0.59 in/min

<sup>5</sup> 0.079 in/min

<sup>6</sup> 120°C/h

<sup>7</sup> Rate A (50°C/h), Loading 2 (50 N)

