

TES J-1200/30 NAT

Techmer Polymer Modifiers - *Acrylonitrile Butadiene Styrene*

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.26		ASTM D792
Molding Shrinkage - Flow (0.125 in)	1.0E-3 to 1.5E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1.40E+6	psi	ASTM D638
Tensile Strength	14000	psi	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	1.30E+6	psi	ASTM D790
Flexural Strength	20000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	2.2	ft·lb/in ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	230	°F	ASTM D648

Notes

¹ Typical properties: these are not to be construed as specifications.

