

Amodel® A-8930 HS

polyphthalamide

Amodel® A-8930 HS is a 30% glass-fiber-reinforced, heat-stabilized polyphthalamide (PPA) with a high heat deflection temperature and very high tensile strength. Excellent creep resistance and low

moisture absorption are also characteristic of this resin.

- Black: A-8930 HS BK 328

General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight	
Additive	• Heat Stabilizer	
Features	• Chemical Resistant • Creep Resistant • Good Dimensional Stability • Good Stiffness • High Heat Resistance	• High Stiffness • High Strength • High Temperature Strength • Low Moisture Absorption
Uses	• Appliances • Automotive Applications • Automotive Electronics • Connectors • Consumer Applications	• Housings • Industrial Applications • Machine/Mechanical Parts • Metal Replacement
Appearance	• Black	
Forms	• Pellets	
Processing Method	• Injection Molding	

Physical	Typical Value	Unit	Test method
Density	1.47	g/cm ³	ISO 1183/A
Molding Shrinkage			ASTM D955
Flow	0.45	%	
Across Flow	0.89	%	
Water Absorption (24 hr)	0.21	%	ASTM D570

Mechanical	Typical Value	Unit	Test method
Tensile Modulus (23°C)	12100	MPa	ISO 527-1
Tensile Stress (Break, 23°C)	194	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	1.8	%	ISO 527-2
Flexural Modulus (23°C)	11400	MPa	ISO 178
Flexural Strain at Break (23°C)	2.6	%	ISO 178
Flexural Strength (Break, 23°C)	288	MPa	ISO 178



Amodel® A-8930 HS

polyphthalamide

Impact	Typical Value	Unit	Test method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	7.5	kJ/m ²	
23°C	7.9	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	46	kJ/m ²	
23°C	48	kJ/m ²	
Notched Izod Impact Strength (23°C)	8.1	kJ/m ²	ISO 180/A
Unnotched Izod Impact Strength			ISO 180/A
-30°C	37	kJ/m ²	
23°C	43	kJ/m ²	

Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	311	°C	ISO 75-2/Bf
1.8 MPa, Unannealed	290	°C	ISO 75-2/ Af
Melting Temperature	323	°C	ISO 11357-3

Injection	Typical Value	Unit
Drying Temperature	120	°C
Drying Time	4.0	hr
Suggested Max Moisture	0.030 to 0.060	%
Rear Temperature	310 to 330	°C
Middle Temperature	315 to 330	°C
Front Temperature	325 to 335	°C
Processing (Melt) Temp	320 to 345	°C
Mold Temperature	150	°C

Injection Notes

Mold Temperature:

- Higher tool temperatures might be required for thin wall sections

Storage:

- Amodel® compounds are shipped in moisture-resistant packages at moisture levels according to specifications. Sealed, undamaged bags should be preferably stored in a dry room at a maximum temperature of 50°C (122°F) and should be protected from possible damage. If only a portion of a package is used, the remaining material should be transferred into a sealable container. It is recommended that Amodel® resins be dried prior to molding following the recommendations found in this datasheet and/or in the Amodel® processing guide.

Notes

Typical properties: these are not to be construed as specifications.

