

Amodel® AT-1001L polyphthalamide

Amodel® AT-1001L is an unreinforced, impact modified polyphthalamide (PPA) resin that exhibits exceptional impact strength at temperatures ranging from room temperature to as low as -40°F (-40°C), which suggests possible applications in ski boots and hockey skates.

Amodel® AT-1001L resin a prime candidate for applications such as anti-friction and wear resistant components, chemical, oil field, automotive and safety equipment.

- Natural: AT-1001 L NT

In addition, its chemical and wear resistance, combined with good mechanical properties, make

General

| | | |
|---------------------------|---|---|
| Material Status | • Commercial: Active | |
| Availability | • Africa & Middle East • Asia Pacific • Europe | • Latin America • North America |
| Additive | • Impact Modifier • Lubricant | • Mold Release |
| Features | • Chemical Resistant • Ductile • Hot Water Moldability • Impact Modified | • Low Temperature Impact Resistance • Low Warpage • Lubricated • Wear Resistant |
| Uses | • Automotive Applications • Automotive Electronics • General Purpose • Housings • Industrial Applications | • Industrial Parts • Machine/Mechanical Parts • Metal Replacement • Oil/Gas Applications |
| RoHS Compliance | • Contact Manufacturer | |
| Automotive Specifications | • ASTM D5336 PPA0110A01080 Color: NT Natural | |
| Appearance | • Natural Color | |
| Forms | • Pellets | |
| Processing Method | • Injection Molding | • Water-Heated Mold Injection Molding |

| Physical | Typical Value | Unit | Test method |
|--------------------------|---------------|-------------------|-------------|
| Density | 1.11 | g/cm ³ | ISO 1183/A |
| Molding Shrinkage | | | ASTM D955 |
| Flow | 1.7 to 2.2 | % | |
| Across Flow | 1.9 to 2.1 | % | |
| Water Absorption (24 hr) | 0.75 | % | ASTM D570 |



Amodel® AT-1001L

polyphthalamide

| Mechanical | Typical Value | Unit | Test method |
|--------------------------|---------------|------|-------------|
| Tensile Modulus | 1900 | MPa | ASTM D638 |
| Tensile Strength (Break) | 62.1 | MPa | ASTM D638 |
| Tensile Elongation | | | ASTM D638 |
| Yield | 6.0 | % | |
| Break | 30 | % | |
| Flexural Modulus | 2210 | MPa | ASTM D790 |
| Flexural Strength | 96.5 | MPa | ASTM D790 |
| Poisson's Ratio | 0.35 | | ASTM E132 |

| Impact | Typical Value | Unit | Test method |
|---------------------|---------------|------|-------------|
| Notched Izod Impact | | | ASTM D256 |
| -40°C | 750 | J/m | |
| 23°C | 1100 | J/m | |

| Thermal | Typical Value | Unit | Test method |
|-----------------------------------|---------------|------|-------------|
| Deflection Temperature Under Load | | | ASTM D648 |
| 1.8 MPa, Annealed, 3.18 mm | 120 | °C | |
| Melting Temperature | 310 | °C | |

Additional Information

Penetration Impact, ASTM D3763, 73°F, Maximum Load: 1100 lbs
Penetration Impact, ASTM D3763, 73°F, Total Energy Absorbed: 40 ft-lbs
Penetration Impact, ASTM D3763, 73°F, Energy to Maximum Load: 30 ft-lbs
Penetration Impact, ASTM D3763, -10°F, Total Energy Absorbed: 40 ft-lbs
Penetration Impact, ASTM D3763, -10°F, Maximum Load: 1260 lbs
Penetration Impact, ASTM D3763, -10°F, Energy to Maximum Load: 30 ft-lbs

| Injection | Typical Value | Unit |
|------------------------|----------------|------|
| Drying Temperature | 110 | °C |
| Drying Time | 4.0 | hr |
| Suggested Max Moisture | 0.030 to 0.060 | % |
| Hopper Temperature | 79 | °C |
| Rear Temperature | 304 to 318 | °C |
| Front Temperature | 316 to 329 | °C |
| Processing (Melt) Temp | 321 to 343 | °C |
| Mold Temperature | > 135 | °C |

Injection Notes

MOLD TEMPERATURE

- If the wall is thick, lower temperatures may be used to prevent ejector pin problems.


STORAGE

- Amodel® compounds are shipped in moisture-resistant packages at moisture levels according to specifications. Sealed, undamaged bags should be preferably stored in a dry room at a maximum temperature of 50°C (122°F) and should be protected from possible damage. If only a portion of a package is used, the remaining material should be transferred into a sealable container. It is recommended that Amodel® resins be dried prior to molding following the recommendations found in this datasheet and/or in the Amodel® processing guide.




Amodel® AT-1001L polyphthalamide

Isothermal Stress vs. Strain (ISO 11403)



Amodel® AT-1001L polyphthalamide

Secant Modulus vs. Strain (ISO 11403)



Amodel® AT-1001L

polyphthalamide

Notes

Typical properties: these are not to be construed as specifications.



YENSQO

