



PP PP

**Polypropylene Impact Copolymer**

**CKR448**

Date of issue: April 2017

**MFR: 4.5 g/10min**

**Density: 0.905 g/cm<sup>3</sup>**

**Features**

- Medium flow
- Suitable for applications where toughness even at low temperatures is required
- Contains a nucleating agent which ensures rapid crystallisation, resulting in an improved impact to stiffness balance as well as shorter cooling times

**Applications**

**Injection moulding**

- Household and domestic articles
- Automotive trim components
- Electrical appliance components
- Outdoor furniture and stadium seating
- Crates and containers
- Buckets / Pails

**Additives**

- Antioxidant
- Processing stabiliser
- Acid scavenger
- Nucleating agent
- Antistatic


Typical properties (not to be construed as specifications)		Value (SI)	Value (English)	Method
<b>Resin Properties</b>	Melt mass-flow rate – MFR (230/2.16)	4.5 g/10min	4.5 g/10min	ISO 1133
	Moulding Shrinkage – $S_{Mp} / S_{Mn}$	1.5 / 1.4 %	1.5 / 1.4 %	ISO 294-4
<b>Physical Properties</b>	Flexural modulus	1 300 MPa	188 600 psi	ISO 178
	Tensile modulus of elasticity	1 350 MPa	195 800 psi	ISO 527-2
	Tensile stress at yield	27 MPa	3 900 psi	ISO 527-2
	Tensile strain at yield	6.0 %	6.0 %	ISO 527-2
	Tensile strain at break	>50 %	>50 %	ISO 527-2
	Charpy notched impact strength (23°C)	15 kJ/m <sup>2</sup>	7.2 ft·lbf/in <sup>2</sup>	ISO 179-1
	Charpy notched impact strength (0°C)	6.0 kJ/m <sup>2</sup>	2.9 ft·lbf/in <sup>2</sup>	ISO 179-1
	Charpy notched impact strength (-20°C)	4.0 kJ/m <sup>2</sup>	1.9 ft·lbf/in <sup>2</sup>	ISO 179-1
	Ball indentation hardness – HB	52 N/mm <sup>2</sup>	7 540 psi	ISO 2039-1
<b>Thermal Properties</b>	Melting temperature – DSC	168°C	335°F	ISO 11357-3
	Heat deflection temperature – HDT / A (1.8 MPa)	50°C	122°F	ISO 75-2
	Heat deflection temperature – HDT / B (0.45 MPa)	83°C	181°F	ISO 75-2
	Vicat softening temperature – VST / A120 (10 N)	152°C	305°F	ISO 306





**Typical processing conditions – CKR448**

**Injection moulding**



**Handling**

Workers should be protected from the possibility of skin or eye contact with molten polymer. Safety glasses are suggested as a minimal protection to prevent possible mechanical or thermal injury to the eyes. Fabrication areas should be ventilated to carry away fumes or vapours. Please consult the material safety data sheet (SDS) for more detailed information.

**Storage**

As ultraviolet light may cause a change in material properties, all resins should be protected from direct sunlight during storage. If stored in cool (<25°C), dry area with low ambient light levels, polyolefin resins are expected to maintain their original material and processing properties for at least 12 months.

**Combustibility**

Polypropylene resins will burn when supplied adequate heat and oxygen. They should be handled and stored away from contact with direct flames and/or other ignition sources. In burning, polypropylene resins contribute high heat and may generate a dense black smoke. Fires can be extinguished by conventional means with water, water mist being preferred. In enclosed areas, fire fighters should be provided with self contained breathing apparatus.

**Conveying**

Conveying equipment should be designed to prevent accumulation of fines and dust particles that are contained in all polypropylene resins. The fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used:

- be equipped with adequate filters
- is operated and maintained in such a manner to ensure no leaks develop
- that adequate grounding exists at all times

It is further recommended that good housekeeping is practiced throughout the facility.

**Regulatory & Legal Compliance**

This material complies with FDA regulation 21 CFR 177.1520 when used unmodified and according to good manufacturing practices for food contact applications. Refer to applicable food contact compliance statement which is available on request.

This material is not medically approved and should therefore not be used in any such application

