

Diofan® B 204

polyvinylidene chloride

Diofan® B 204 is a PVDC water-based dispersion with outstanding impermeability to gases and

moisture. It is particularly recommended for coatings on plastic films.

General

Material Status	• Commercial: Active	
Availability	• Asia Pacific • Europe	• Latin America • North America
Uses	• Coating Applications	
Agency Ratings	• EC 1907/2006 (REACH) • EU No 10/2011	• FDA ¹
Appearance	• Milky White	
Forms	• Liquid	

Physical

Typical Value Unit

Density		
Coated Film (dry)	1.65 g/cm ³	
Dispersion (wet)	1.27 g/cm ³	
Emulsion Type	Anionic	
Filmability - Film Forming Temperature	14 °C	
pH	1.5	
Solids Content	51 %	
Surface Tension - Foaming tendency	45 mN/m	
Viscosity - Dynamic (20°C)	17 mPa·s	

Mechanical

Typical Value Unit

Test method

Coefficient of Friction vs. Itself - Dynamic	0.35	ASTM D1894
---	------	------------

Films

Typical Value Unit

Test method

Water Vapor Transmission Rate ² 38°C, 90% RH, 1.0 µm	11 g/m ² /24 hr	ASTM F1249
Oxygen Transmission Rate - (25°C, 85% RH, 1.0 µm) ²	11 cm ³ /m ² /bar/ 24 hr	ASTM D3985
Heat Seal Maximum Resistance - 20 PSI - 1s - 1 heated jaw	1.0 N/cm	
Heat Seal Threshold - 0.4 N/cm; 20 PSI - 1s - 1 heated jaw	124 °C	

Additional Information

Typical Value Unit

Shelf Life (23°C)	12 month	
-------------------	----------	--



Diofan® B 204

polyvinylidene chloride

DELIVERY AND STORAGE

- Diofan® B 204 is delivered in bulk or in Intermediate Bulk Containers (IBC). Bulk supplied latex should be stored in reservoirs made of suitable stainless steel, HDPE, rigid PVC or glass fiber-reinforced polyester.
- Contact of anionic Diofan® dispersion with metals like iron, zinc, aluminum and copper as well as alloys such as brass and bronze must be avoided.
- Keep the vessels tightly closed to prevent drying through evaporation. Store the product ideally between 5°C and 30°C (41 °F and 86°F) to avoid degradation.

PROCESSING - DRYING

- Diofan® B 204 can be processed with different coating techniques, including reverse gravure roll and air knife coating systems.
- When coated on plastic films, Diofan® B 204 should be formulated with wax and silica in order to improve the blocking and slip properties of the finished coating.
- Diofan® coatings requires adequate drying conditions, since in general higher temperatures will contribute to better barrier properties.

FOOD AND DRUG LEGISLATIONS

- Some agency ratings are listed on page 1. Necessary certification will be provided upon request.

ISO CERTIFICATION

- The implemented management system for the production, internal transfer and delivery, design and development of Diofan® vinylidene chloride copolymers (PVDC) produced in Tavaux has been assessed and found to meet the requirements of ISO 9001: 2008, ISO 14001: 2004 and OHSAS 18001: 2007.
-

Notes

Typical properties: these are not to be construed as specifications.

¹ Please contact your Account Manager to request an EU food contact and/or FDA letter which provides the specifications for compliance with these regulations.

² Coating on PET film. Diofan® coating weight dry: 2.5 g/m²; used additive package: 5 g/kg wax + 5 g/kg silica

