

Ecologue™ PA-757 M90

CHI MEI CORPORATION - Acrylonitrile Butadiene Styrene

General Information

Product Description

Ecologue PCR ABS PA-757 M90

Product Description: PCR content 90%

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Recycled Content	• Post-Consumer (PCR), 90%		
Resin ID (ISO 1043)	• >ABS(REC90)<		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.05	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	30	cm ³ /10min	ISO 1133
Molding Shrinkage	0.40 to 0.70	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	5800	psi	ISO 527-2/50
Tensile Stress (Break)	4350	psi	ISO 527-2/50
Tensile Strain (Break)	30	%	ISO 527-2/50
Flexural Modulus ²	319000	psi	ISO 178
Flexural Stress ²	8700	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	7.1	ft-lb/in ²	ISO 179
Notched Izod Impact Strength (73°F)	7.1	ft-lb/in ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	167	°F	ISO 75-2/A
Vicat Softening Temperature	221	°F	ISO 306/A50
CLTE - Flow	4.8E-5	in/in/°F	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		UL 94

Notes

¹ Typical properties: these are not to be construed as specifications.

² 0.079 in/min

