



Sasol Polymers LLDPE: HF121 Density: 0.924 g/cm³ MFI: 1.0 g/10min

Features

- Hexene copolymer
- Outstanding mechanical properties
- Excellent drawdown
- Good heat sealing range

Applications

- General packaging (30μm to 70μm)
- Blending into LDPE

Additives

- Antioxidant
- Medium anti block
- Medium slip

Material properties (typical values not to be construed as specifications)

	Value	Unit	Test method
MFI (190°C/2.16kg)	1.0	g/10 min	ASTM D1238
Nominal density	0.924	g/cm ³	ASTM D1505
Tensile strength at yield MD	13	MPa	ASTM D882
TD	11	MPa	ASTM D882
Tensile strength at break MD	34	MPa	ASTM D882
TD	25	MPa	ASTM D882
Elongation MD	525	%	ASTM D882
TD	651	%	ASTM D882
Tear strength MD	9	g/μm	ASTM D1922
TD	28	g/μm	ASTM D1922
Impact strength (F ₅₀)	144	g	ASTM D1709
Haze	12	%	ASTM D1003
Gloss @ 45°	51	units	ASTM D2457
Blocking	19	g	ASTM 3354
Coefficient of friction μS	0.14	units	ASTM D1894
μD	0.14	units	ASTM D1894

The above values were calculated from data for 30μm film produced on a 75mm Barmag extruder with 190°C melt temperature using a 2:1 blow ratio and a die gap of 3.0mm.



Product data sheet - HF121



Typical processing conditions

Blown film

°C	H	1	2	3	4	D
220						
200						
180						
160						
140						



HF121 should be processed on equipment designed or retrofitted for LLDPE, i.e.

- Increased die gap unless a processing aid is incorporated.
- Suitable screw e.g. Sasol Polymers design full length general purpose pitch.
- Aerodynamic cooling systems.

Recommended melt temperature: 190°C
Recommended screen pack: 20/40/20 BS mesh.
Blow ratios of greater than 2:1 recommended.

Packaging

Sasol Polymers polyolefin resins are supplied in pellet form packed in 25kg bags. Alternative packaging modes for polypropylene resins are available for selected grades.

Handling

Workers should be protected from the possibility of skin or eye contact with molten polymer. Safety glasses and heat resistant gloves are suggested as a minimal precaution to prevent possible mechanical or thermal injuries to the eyes and skin. Fabrication areas should be ventilated to carry away fumes or vapours.

Conveying equipment should be designed to prevent accumulation of fines or dust particles that are contained in all polyolefin resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. Sasol Polymers recommend the conveying system used:

- be equipped with adequate filters
- is operated and maintained in such a manner to ensure no leaks develop
- that adequate grounding exists at all times

Sasol Polymers further recommend that good housekeeping be practised throughout the manufacturing facility. Polymer pellets may pose a slippage hazard if spilled.

Storage

As ultraviolet light may cause a change in the material properties, all polyolefin resins should be protected from direct sunlight during storage. Under cool, dry, dark conditions Sasol Polymers polyolefin resins are expected to maintain their original material and processing properties for at least 18 months.

