



Polypropylene Homopolymer

HKQ156

MFR: 3.0 g/10min

Density: 0.905 g/cm³

Features

- Low flow
- Nucleated with mould release
- Especially suitable for thermoforming applications where very good clarity is required
- A very good balance between stiffness and impact resistance
- Excellent colour

Applications

- Thermoformed cups
- Clam shells
- Food trays
- Lidding

Additives

- Antioxidant
- Processing stabiliser
- Acid scavenger
- Nucleation
- Mould release

Typical properties (not to be construed as specifications)		Value (SI)	Value (English)	Method
Resin Properties	Melt mass-flow rate – MFR (230/2.16)	3.0 g/10min	3.0 g/10min	ISO 1133
	Moulding Shrinkage – S_{Mp} / S_{Mn}	1.5 / 1.4 %	1.5 / 1.4 %	ISO 294-4
Physical Properties	Flexural modulus	1 650 MPa	239 315 psi	ISO 178
	Tensile modulus of elasticity	1 750 MPa	253 815 psi	ISO 527-2
	Tensile stress at yield	37 MPa	5 365 psi	ISO 527-2
	Tensile strain at yield	8.5 %	8.5 %	ISO 527-2
	Tensile strain at break	>50 %	>50 %	ISO 527-2
	Charpy notched impact strength (23°C)	5.5 kJ/m ²	2.6 ft·lbf/in ²	ISO 179-1
	Ball indentation hardness – HB	72 N/mm ²	10 440 psi	ISO 2039-1
Thermal Properties	Melting temperature – DSC	168°C	334°F	ISO 11357-3
	Recrystallization temperature – DSC	125°C	257°F	ISO 11357-3
	Heat deflection temperature – HDT/A (1.8 MPa)	55°C	131°F	ISO 75-2
	Heat deflection temperature – HDT/B (0.45 MPa)	95°C	203°F	ISO 75-2
	Vicat softening temperature – VST/A120 (10 N)	155°C	311°F	ISO 306
Other Properties	Haze (1 mm plaque injection moulded @ 200°C)	24%	24%	ISO 14782
	Gloss (60°)	95 GU	95 GU	ISO 2813






Typical processing conditions – HKQ156

Sheet extrusion

MELT TEMPERATURE 230 - 250°C



Roll-stack temperature guideline: 60/70/60°C

Handling

Workers should be protected from the possibility of skin or eye contact with molten polymer. Safety glasses are suggested as a minimal protection to prevent possible mechanical or thermal injury to the eyes. Fabrication areas should be ventilated to carry away fumes or vapours. Please consult the material safety data sheet (SDS) for more detailed information.

Storage and Shelf Life

As ultraviolet light may cause a change in material properties, all resins should be protected from direct sunlight during storage. If stored in cool (<25°C), dry area with low ambient light levels, polyolefin resins are expected to maintain their original material and processing properties for at least 12 months from production.

Combustibility

Polypropylene resins will burn when supplied adequate heat and oxygen. They should be handled and stored away from contact with direct flames and/or other ignition sources. In burning, polypropylene resins contribute high heat and may generate a dense black smoke. Fires can be extinguished by conventional means with water, water mist being preferred. In enclosed areas, fire fighters should be provided with self contained breathing apparatus.

Conveying

Conveying equipment should be designed to prevent accumulation of fines and dust particles that are contained in all polypropylene resins. The fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used:

- be equipped with adequate filters
- is operated and maintained in such a manner to ensure no leaks develop
- that adequate grounding exists at all times

It is further recommended that good housekeeping is practiced throughout the facility.

Regulatory & Legal Compliance

This material complies with FDA regulation 21 CFR 177.1520 when used unmodified and according to good manufacturing practices for food contact applications. Refer to applicable food contact compliance statement which is available on request.

This material is not medically approved and should therefore not be used in any such application

