



Polypropylene Homopolymer

**HNR101**

**MFR: 12 g/10min**

**Density: 0.905 g/cm<sup>3</sup>**

**Features**

- High flow
- Suitable for short spin and long spin staple fibre applications
- Offers easy extrusion processibility when producing:
  - Medium to high denier fibre
  - Continuous multifilament (CF) on multi position spin/draw/wind or short spin/warp draw/wind processes

**Applications**

**Extrusion**

- Needle punched carpets
- Filtration cloth
- Sewing yarns
- Narrow weave strapping

**Additives**

- Antioxidant (anti-gas fading)
- Processing stabiliser
- Acid scavenger


Typical properties (not to be construed as specifications)		Value (SI)	Value (English)	Method
<b>Resin Properties</b>	Melt mass-flow rate – MFR (230/2.16)	12 g/10min	12 g/10min	ISO 1133
<b>Physical Properties</b>	Flexural modulus	1 500 MPa	217 560 psi	ISO 178
	Tensile modulus of elasticity	1 550 MPa	224 810 psi	ISO 527-2
	Tensile stress at yield	34 MPa	4 930 psi	ISO 527-2
	Tensile strain at yield	8.5 %	8.5 %	ISO 527-2
	Tensile strain at break	>50 %	>50 %	ISO 527-2
	Charpy notched impact strength (23°C)	2.8 kJ/m <sup>2</sup>	1.4 ft.lbf/in <sup>2</sup>	ISO 179-1
	Ball indentation hardness – HB	70 N/mm <sup>2</sup>	10 150 psi	ISO 2039-1
<b>Thermal Properties</b>	Melting temperature – DSC	166°C	332°F	ISO 11357-3
	Heat deflection temperature – HDT / A (1.8 MPa)	53°C	127°F	ISO 75-2
	Heat deflection temperature – HDT / B (0.45 MPa)	85°C	185°F	ISO 75-2
	Vicat softening temperature – VST / A120 (10 N)	154°C	309°F	ISO 306





**Typical processing conditions – HNR101**

**Fibre extrusion**



**Handling**

Workers should be protected from the possibility of skin or eye contact with molten polymer. Safety glasses are suggested as a minimal protection to prevent possible mechanical or thermal injury to the eyes. Fabrication areas should be ventilated to carry away fumes or vapours. Please consult the material safety data sheet (SDS) for more detailed information.

**Storage**

As ultraviolet light may cause a change in material properties, all resins should be protected from direct sunlight during storage. If stored in cool (<25°C), dry area with low ambient light levels, polyolefin resins are expected to maintain their original material and processing properties for at least 12 months.

**Combustibility**

Polypropylene resins will burn when supplied adequate heat and oxygen. They should be handled and stored away from contact with direct flames and/or other ignition sources. In burning, polypropylene resins contribute high heat and may generate a dense black smoke. Fires can be extinguished by conventional means with water, water mist being preferred. In enclosed areas, fire fighters should be provided with self contained breathing apparatus.

**Conveying**

Conveying equipment should be designed to prevent accumulation of fines and dust particles that are contained in all polypropylene resins. The fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used:

- be equipped with adequate filters
- is operated and maintained in such a manner to ensure no leaks develop
- that adequate grounding exists at all times

It is further recommended that good housekeeping is practiced throughout the facility.

**Regulatory & Legal Compliance**

This material complies with FDA regulation 21 CFR 177.1520 when used unmodified and according to good manufacturing practices for food contact applications. Refer to applicable food contact compliance statement which is available on request.

This material is not medically approved and should therefore not be used in any such application.

