

## Iupilon™ GSH2020R2

Mitsubishi Engineering-Plastics Corp - Polycarbonate

### General Information

#### Product Description

Glass Fiber Reinforced, GF20%

#### General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight
Uses	• General Purpose

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.35	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	8.5	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	8.0	cm <sup>3</sup> /10min	ISO 1133
Molding Shrinkage			Internal Method
Across Flow	0.30 to 0.50	%	
Flow	0.10 to 0.30	%	
Water Absorption (Saturation, 73°F)	0.11	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	899000	psi	ISO 527-1/1
Tensile Stress (Break)	15100	psi	ISO 527-2/5
Tensile Strain (Break)	3.2	%	ISO 527-2/5
Flexural Modulus <sup>2</sup>	841000	psi	ISO 178
Flexural Stress <sup>2</sup>	23200	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	6.2	ft·lb/in <sup>2</sup>	ISO 179
Charpy Unnotched Impact Strength (73°F)	26	ft·lb/in <sup>2</sup>	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	295	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	289	°F	ISO 75-2/A
CLTE - Flow	1.4E-5	in/in/°F	ISO 11359-2
CLTE - Transverse	3.5E-5	in/in/°F	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (CTI)	PLC 3		UL 746A
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.016 in)	HB		UL 94

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature - Hot Air Dryer	248	°F
Drying Time - Hot Air Dryer	4.0 to 8.0	hr
Rear Temperature	554 to 590	°F
Middle Temperature	554 to 590	°F
Front Temperature	554 to 590	°F
Nozzle Temperature	554 to 590	°F
Mold Temperature	176 to 248	°F

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 0.079 in/min

