

KIBIPOL® PR-1205

CHI MEI CORPORATION - *Solution Styrene Butadiene Rubber*

General Information

Product Description

SSBR

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
RoHS Compliance	• RoHS Compliant		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.912		ASTM D792
Mooney Viscosity	42 to 52	MU	ASTM D1646
Solution Viscosity ²	10	mPa·s	ASTM D445
Ash Content	< 0.10	wt%	ASTM D5667
CIS Content	35	%	
Vinyl Content	12 to 15	%	
Volatile Matter	< 0.75	wt%	ASTM D5668
Optical	Nominal Value	Unit	Test Method
APHA Color	< 10.0		ASTM D1209
Additional Information	Nominal Value	Unit	Test Method
Bale Weight	35000	g	
BD/SM Ratio	75/25	%	ASTM D5775
Wrapping Film	LDPE or PS		

Notes

¹ Typical properties: these are not to be construed as specifications.

² 5% Styrene

