

KIBIPOL® PR-303

CHI MEI CORPORATION - *Solution Styrene Butadiene Rubber*

General Information

Product Description

SSBR

General

Material Status	<ul style="list-style-type: none"> Commercial: Active 		
Availability	<ul style="list-style-type: none"> Africa & Middle East Asia Pacific 	<ul style="list-style-type: none"> Europe Latin America 	<ul style="list-style-type: none"> North America
RoHS Compliance	<ul style="list-style-type: none"> RoHS Compliant 		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Mooney Viscosity	40 to 50	MU	ASTM D1646
Volatile Matter	< 0.75	wt%	ASTM D5668
Optical	Nominal Value	Unit	Test Method
APHA Color	< 10.0		ASTM D1209
Additional Information	Nominal Value	Unit	Test Method
Bale Weight	35000	g	
BD/SM Ratio	54/46	%	ASTM D5775
Wrapping Film	LDPE		

Notes

¹ Typical properties: these are not to be construed as specifications.

