



LDPE LDPE

Low Density Polyethylene

LF2220

Melt Index: 2.0 g/10min

Density: 0.922 g/cm<sup>3</sup>

Features

- Tubular Resin
- Good flexibility

Applications

- Blow moulded bottles and tubes
- Pool hose
- Extruded profiles
- Foamed polyethylene sheeting and profiles
- Small injection moulded parts

Additives

- Antioxidant

Typical properties (not to be construed as specifications)		Value (SI)	Value (English)	Method
Resin Properties	Melt Index (190°C/2.16kg)	2.0 g/10min	2.0 g/10min	ASTM D1238
	Nominal density	0.922 g/cm <sup>3</sup>	0.922 g/cm <sup>3</sup>	ASTM D1505
Product Properties	Tensile strength at yield	12 MPa	1740 psi	ASTM D638 <sup>1)</sup>
	Tensile strength at break	12 MPa	1740 psi	ASTM D638 <sup>1)</sup>
	Elongation at break	500 %	500 %	ASTM D638 <sup>1)</sup>
	Flexural modulus	250 MPa	36250psi	ASTM D790
	ESCR F <sub>50</sub>	0.2 hr	0.2 hr	ASTM D1693 <sup>2)</sup>
	Shore D Hardness	53	53	ASTM D2240
	Vicat softening temperature	96 °C	96 °C	ASTM D1525

1) Crosshead speed 500mm/min  
 2) 100% Igepal CO630






**Blow moulding**

MELT TEMPERATURE 160 - 200°C


M	D	°C	4	3	2	1	H
		300					
		260					
		220					
		180					
		140					
		100					
		60					
		20					



**Extrusion**

MELT TEMPERATURE 180 - 210°C


D	°C	5	4	3	2	1	H
	300						
	260						
	220						
	180						
	140						
	100						
	60						
	20						



**Injection moulding**

MELT TEMPERATURE 200 - 240°C

M	°C	N	4	3	2	1	H
	300						
	260						
	220						
	180						
	140						
	100						
	60						
	20						



**Processing**

LF2220 can be processed on all standard processing equipment. Processing conditions need to be optimised, but the melt temperatures should typically be 160°C to 200°C for blow moulding and extrusion, and 200°C to 240°C for injection moulding.

**Handling**

Workers should be protected from the possibility of skin or eye contact with molten polymer. Safety glasses are suggested as a minimal protection to prevent possible mechanical or thermal injury to the eyes. Fabrication areas should be ventilated to carry away fumes or vapours. Please consult the material safety data sheet (SDS) for more detailed information.

**Storage**

As ultraviolet light may cause a change in the material, all resins should be protected from direct sunlight during storage. If stored in cool (<25°C), dry area with low ambient light levels, polyolefin resins are expected to maintain their original material and processing properties for at least 12 months.

**Combustibility**

Polyethylene resins will burn when supplied adequate heat and oxygen. They should be handled and stored away from contact with direct flames and/or other ignition sources. In burning, polyethylene resins contribute high heat and may generate a dense black smoke. Fires can be extinguished by conventional means with water and water mist preferred. In enclosed areas, fire fighters should be provided with self contained breathing apparatus.

**Conveying**

Conveying equipment should be designed to prevent accumulation of fines and dust particles that are contained in all polyethylene resins. The fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used:

- be equipped with adequate filters
- is operated and maintained in such a manner to ensure no leaks develop
- that adequate grounding exists at all times

It is further recommended that good housekeeping is practiced throughout the facility.

**Regulatory & Legal Compliance**

This material complies with FDA regulation 21 CFR 177.1520 when used unmodified and according to good manufacturing practices for food contact applications. Refer to applicable food contact compliance statement which is available on request. This material is not medically approved and should therefore not be used in any such application.

