

## Optiflex TPV80A

The Materials Group - *Thermoplastic Vulcanizate*

### General Information

#### General

Material Status	• Commercial: Active
Availability	• North America
Features	• Excellent Processability
Appearance	• Black • Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	0.970	g/cm <sup>3</sup>	ISO 1183
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (Break)	1450	psi	ISO 37
Tensile Elongation (Break)	480	%	ISO 37
Compression Set (257°F, 70 hr)	50	%	ISO 815
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	80		ISO 868

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature	140	°F
Drying Time	3.0	hr
Suggested Max Moisture	0.080	%
Rear Temperature	360	°F
Middle Temperature	370	°F
Front Temperature	380	°F
Nozzle Temperature	390	°F
Processing (Melt) Temp	390	°F
Mold Temperature	> 120	°F

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

