

RADILON A HSX88 333 NER

*Material code**Colour code*

DESCRIPTION

PA66 injection moulding grade. Toughened. Black colour.

Suitable for parts requiring improved impact resistance.

ISO 1043 : PA66-I

MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.15%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more.

Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

Processing Parameters

Melt Temperature:	Mold Temperature:	Injection Speed:
270 ÷ 290 °C	70 ÷ 90 °C	Medium

PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet

RoHS compliant 2011/65/UE and following amendments





Technical data sheet

RADILON A HSX88 333 NER

Material code

Colour code

PROPERTY		STANDARD	UNIT	VALUE	
				DAM*	Cond**
Physical Properties					
Density		ISO 1183	Kg/m ³	1100	
Moulding shrinkage – Parallel / Normal	290/70/60***	ISO 294-4	%	1,5 / 1,4	
Moisture absorption 23°C – 50%RH	2mm thk	ISO 62	%	2	
Water absorption, immersion at 23°C	2mm thk	ISO 62	%	7.6	
Melt Flow Rate	275°C / 5kg	ISO 1133	g/10'	40	
Mechanical Properties					
Tensile Modulus	1mm/min	ISO 527-2/1A	MPa	2200	1250
Stress at Yield	50mm/min	ISO 527-2/1A	MPa	60	43
Yield Strain	50mm/min	ISO 527-2/1A	%	8	25
Nominal Strain at Break	50mm/min	ISO 527-2/1A	%	40	>50
Flexural Modulus	2mm/min	ISO 178	MPa	2100	
Flexural Strength	2mm/min	ISO 178	MPa	80	
Charpy Notched Impact Strength	+23°C	ISO 179/1 eA	KJ/m ²	40	85
Thermal Properties					
Melting Temperature	10°C/min	ISO 11357-1-3	°C	260	
Heat Deflection Temperature	1.8 MPa	ISO 75/2 A f	°C	55	
Heat Deflection Temperature	0.45 MPa	ISO 75/2 B f	°C	170	
Vicat Softening Temperature	50°C/h	ISO 306/B50 50N	°C	210	
Flammability Properties					
Flammability	0.8mm	UL 94	class	HB	
Glow Wire Flammability Index	2mm	IEC 60695-2-12	°C/mm	650	
Automotive interior flammability	3mm thk	ISO 3795	mm/min	< 30	
Electrical Properties					
Volume resistivity	500V	IEC 60093	ohm · m	1 E+13	1 E+11
Surface resistivity	500V	IEC 60093	ohm	1 E+12	1 E+10

*DAM = Dry As Moulded state **Cond = Conditioned state similar to ISO 1110 ***Melt Temp [°C] / Mold Temp [°C] / Cavity press [MPa]

