

# RADILON A RV400W 333 NER

Material code

Colour code

PROVISIONAL

## DESCRIPTION

PA66 40% glass fiber reinforced injection moulding grade. Heat stabilized. Black colour.

Suitable for parts requiring high stiffness, good mechanical resistance and excellent heat ageing properties retention.

ISO 1043 : PA66-T GF40

## MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.15%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more.

Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

### Processing Parameters

Melt Temperature:	Mold Temperature:	Injection Speed:
280 ÷ 300 °C	80 ÷ 100 °C	Medium-high

## PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet

RoHS compliant 2011/65/UE and following amendments



## Technical data sheet

PROVISIONAL

# RADILON A RV400W 333 NER

Material code

Colour code

PROPERTY	UNIT	STANDARD	VALUE	
			DAM*	Cond**
<b>Physical Properties</b>				
Density		ISO 1183	Kg/m <sup>3</sup>	1470
Moisture absorption 23°C – 50%RH	2mm thk	ISO 62	%	1.3
Water absorption, immersion at 23°C	2mm thk	ISO 62	%	5.5
<b>Mechanical Properties</b>				
Tensile Modulus	1mm/min	ISO 527-2/1A	MPa	12800 10500
Stress at Break	5mm/min	ISO 527-2/1A	MPa	210 145
Strain at Break	5mm/min	ISO 527-2/1A	%	3 4
Flexural Modulus	2mm/min	ISO 178	MPa	11600
Flexural Strength	2mm/min	ISO 178	MPa	290
Charpy Impact Strength	+23°C	ISO 179/1 eU	KJ/m <sup>2</sup>	100 105
Charpy Impact Strength	-30°C	ISO 179/1 eU	KJ/m <sup>2</sup>	80
Charpy Notched Impact Strength	+23°C	ISO 179/1 eA	KJ/m <sup>2</sup>	14 17
Charpy Notched Impact Strength	-30°C	ISO 179/1 eA	KJ/m <sup>2</sup>	10
<b>Thermal Properties</b>				
Melting Temperature	10°C/min	ISO 11357-1-3	°C	260
Heat Deflection Temperature	1.8 MPa	ISO 75/2 A f	°C	250
Heat Deflection Temperature	0.45 MPa	ISO 75/2 B f	°C	255
Vicat Softening Temperature	50°C/h	ISO 306/B50 50N	°C	250
<b>Flammability Properties</b>				
Flammability	0.8mm	UL 94	class	HB
Glow Wire Flammability Index	2mm	IEC 60695-2-1/2	°C/mm	700
Automotive interior flammability	Burn rate	FMVSS302	mm/min	0
<b>Electrical Properties</b>				
Volume resistivity	500V	IEC 60093	ohm · m	1 E+13 1 E+11
Surface resistivity	500V	IEC 60093	ohm	1 E+12 1 E+10

\*DAM = Dry As Moulded state \*\*Cond = Conditioned state similar to ISO 1110 \*\*\*Melt Temp [°C] / Mold Temp [°C] / Cavity press [MPa]

