

# RADILON A RV500K 333 NER

*Material code**Colour code*

## DESCRIPTION

PA66 50% glass fiber reinforced injection moulding grade. Heat stabilized. Black colour.

Suitable for parts requiring very high stiffness and high mechanical resistance, as in case of metal replacement applications. Good resistance to thermal ageing.

ISO 1043 : PA66-T GF50

## MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.15%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more.

Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

### Processing Parameters

Melt Temperature:	Mold Temperature:	Injection Speed:
290 ÷ 305 °C	80 ÷ 100 °C	Medium-high

## PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet



Underwriters Laboratories Inc. certified material. File number: E116324 [www.ul.com](http://www.ul.com)

RoHS compliant 2002/95/CE and following amendments



## Technical data sheet

# RADILON A RV500K 333 NER

Material code      Colour code

PROPERTY	UNIT	STANDARD	VALUE	
			DAM*	Cond**
<b>Physical Properties</b>				
Density		ISO 1183	Kg/m <sup>3</sup>	1580
Moisture absorption 23°C – 50%RH	2mm thk	ISO 62	%	1.1
Water absorption, immersion at 23°C	2mm thk	ISO 62	%	4.6
<b>Mechanical Properties</b>				
Tensile Modulus	1mm/min	ISO 527-2/1A	MPa	16200
Stress at Break	5mm/min	ISO 527-2/1A	MPa	215
Strain at Break	5mm/min	ISO 527-2/1A	%	2,5
Flexural Modulus	2mm/min	ISO 178	MPa	14500
Flexural Strength	2mm/min	ISO 178	MPa	320
Charpy Impact Strength	+23°C	ISO 179/1 eU	KJ/m <sup>2</sup>	85
Charpy Notched Impact Strength	+23°C	ISO 179/1 eA	KJ/m <sup>2</sup>	13
Charpy Notched Impact Strength	-30°C	ISO 179/1 eA	KJ/m <sup>2</sup>	
<b>Thermal Properties</b>				
Melting Temperature	10°C/min	ISO 11357-1-3	°C	260
Heat Deflection Temperature	1.8 MPa	ISO 75/2 A f	°C	245
Vicat Softening Temperature	50°C/h	ISO 306/B50 50N	°C	250
<b>Flammability Properties</b>				
Flammability	0.8mm	UL 94	class	HB
Glow Wire Flammability Index	2mm	IEC 60695-2-1/2	°C/mm	700
Automotive interior flammability	Burn rate	FMVSS302	mm/min	0
<b>Electrical Properties</b>				
Volume resistivity	500V	IEC 60093	ohm · m	1 E+13    1 E+11
Surface resistivity	500V	IEC 60093	ohm	1 E+12    1 E+10
Comparative Tracking Index	Sol.A	IEC 60112	V	500

\*DAM = Dry As Moulded state    \*\*Cond = Conditioned state similar to ISO 1110    \*\*\*Melt Temp [°C] / Mold Temp [°C] / Cavity press [MPa]

