

# RADILON A RV500RW 182 NAT 5346

*Material code**Colour code*

PROVISIONAL

## DESCRIPTION

PA66 50% glass fiber reinforced injection moulding grade. Heat stabilized. Natural colour.

Suitable for technical parts requiring very high stiffness and high mechanical resistance. Excellent heat ageing properties retention, improved welding lines strength. Especially fit for demanding metal replacement applications.

ISO 1043 : PA66-T GF50

## MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.15%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more.

Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

### Processing Parameters

Melt Temperature:	Mold Temperature:	Injection Speed:
280 ÷ 300 °C	80 ÷ 100 °C	High

## PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet

RoHS compliant 2002/95/CE and following amendments



## Technical data sheet

PROVISIONAL

# RADILON A RV500RW 182 NAT 5346

Material code

Colour code

PROPERTY		STANDARD	UNIT	VALUE	
				DAM*	Cond**
<b>Physical Properties</b>					
Density		ISO 1183	Kg/m <sup>3</sup>	1580	
Moisture absorption 23°C – 50%RH	2mm thk	ISO 62	%	1,1	
Water absorption, immersion at 23°C	2mm thk	ISO 62	%	4	
<b>Mechanical Properties</b>					
Tensile Modulus	1mm/min	ISO 527-2/1A	MPa	17500	
Stress at Break	5mm/min	ISO 527-2/1A	MPa	245	
Strain at Break	5mm/min	ISO 527-2/1A	%	2,9	
Flexural Modulus	2mm/min	ISO 178	MPa	16000	
Flexural Strength	2mm/min	ISO 178	MPa	385	
Charpy Impact Strength	+23°C	ISO 179/1 eU	KJ/m <sup>2</sup>	95	
<b>Thermal Properties</b>					
Melting Temperature	10°C/min	ISO 11357-1-3	°C	260	
Heat Deflection Temperature	1.8 MPa	ISO 75/2 A f	°C	255	
Heat Deflection Temperature	8 MPa	ISO 75/2 C f	°C	215	
Vicat Softening Temperature	50°C/h	ISO 306/B50 50N	°C	255	
<b>Flammability Properties</b>					
Flammability	0.8mm	UL 94	class	HB	
Automotive interior flammability	Burn rate	FMVSS302	mm/min	0	
<b>Electrical Properties</b>					
Volume resistivity	500V	IEC 60093	ohm · m	1 E+13	1 E+11
Surface resistivity	500V	IEC 60093	ohm	1 E+12	1 E+10

The characteristics shown here must be considered purely provisional and indicative for a product at developmental stage.

\*DAM = Dry As Moulded state \*\*Cond = Conditioned state similar to ISO 1110 \*\*\*Melt Temp [°C] / Mold Temp [°C] / Cavity press [MPa]

