

# RADILON A 35 990 E GRI

Material code      Colour code

## DESCRIPTION

PA66 medium-high viscosity extrusion grade, also suitable for injection moulding. Natural grey colour.

Suitable for extrusion processes where medium-high viscosity is required. Also suitable for injection moulding of high thickness parts. Material designed for components requiring low friction coefficient and improved tribological properties. Typical application: cable jacketing.

ISO 1043 : PA66

## MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.15%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more.

Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

### Processing Parameters

Melt Temperature:	Mold Temperature:	Injection Speed:	Extrusion Temp: 270 ÷ 290°C
270 ÷ 290 °C	70 ÷ 90 °C	Medium	

## PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet

RoHS compliant 2002/95/CE and following amendments



## Technical data sheet

# RADILON A 35 990 E GRI

Material code      Colour code

PROPERTY		STANDARD	UNIT	VALUE	
				DAM*	Cond**
<b>Physical Properties</b>					
Density		ISO 1183	Kg/m <sup>3</sup>	1140	
Water absorption, immersion at 23°C	2mm thk	ISO 62	%	8	
<b>Mechanical Properties</b>					
Tensile Modulus	1mm/min	ISO 527-2/1A	MPa	3300	2300
Stress at Yield	50mm/min	ISO 527-2/1A	MPa	80	65
Yield Strain	50mm/min	ISO 527-2/1A	%	5	20
Nominal Strain at Break	50mm/min	ISO 527-2/1A	%	20	30
Flexural Modulus	2mm/min	ISO 178	MPa	2800	
Flexural Strength	2mm/min	ISO 178	MPa	105	
Charpy Notched Impact Strength	+23°C	ISO 179/1 eA	KJ/m <sup>2</sup>	5.5	7
Charpy Notched Impact Strength	-30°C	ISO 179/1 eA	KJ/m <sup>2</sup>	4.5	
<b>Thermal Properties</b>					
Melting Temperature	10°C/min	ISO 11357-1-3	°C	260	
Heat Deflection Temperature	1.8 MPa	ISO 75/2 A f	°C	90	
Heat Deflection Temperature	0.45 MPa	ISO 75/2 B f	°C	195	
Vicat Softening Temperature	50°C/h	ISO 306/B50 50N	°C	235	
<b>Flammability Properties</b>					
Flammability	0.8mm	UL 94	class	HB	
Automotive interior flammability	Burn rate	FMVSS302	mm/min	0	
<b>Electrical Properties</b>					
Volume resistivity	500V	IEC 60093	ohm · m	1 E+13	1 E+11
Surface resistivity	500V	IEC 60093	ohm	1 E+12	1 E+10
Comparative Tracking Index	Sol.A	IEC 60112	V	600	

\*DAM = Dry As Moulded state \*\*Cond = Conditioned state similar to ISO 1110 \*\*\*Melt Temp [°C] / Mold Temp [°C] / Cavity press [MPa]

