

# RADILON A 50W 100 M NAT 5770

Material code      Colour code

PROVISIONAL

## DESCRIPTION

PA66 very high viscosity extrusion grade. Heat stabilized. Natural colour.

Suitable for extrusion processes where very high impact resistance and excellent heat ageing properties are required. Also suitable for injection moulding of high thickness items.

ISO 1043 : PA66-T

## MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.15%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more.

Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

### Processing Parameters

Melt Temperature:	Mold Temperature:	Injection Speed:
280 ÷ 300 °C	70 ÷ 90 °C	Medium

## PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet

RoHS compliant 2002/95/CE and following amendments





# Technical data sheet

PROVISIONAL

## RADILON A 50W 100 M NAT 5770

Material code

Colour code

PROPERTY	STANDARD	UNIT	VALUE	
			DAM*	Cond**
<b>Physical Properties</b>				
Density	ISO 1183	Kg/m <sup>3</sup>	1140	
Viscosity Index (Sulfuric Acid)	ISO 307	ml/g	295	
<b>Mechanical Properties</b>				
Tensile Modulus	1mm/min	ISO 527-2/1A	MPa	3100
Stress at Yield	50mm/min	ISO 527-2/1A	MPa	80
Yield Strain	50mm/min	ISO 527-2/1A	%	4
Nominal Strain at Break	50mm/min	ISO 527-2/1A	%	40
Flexural Modulus	2mm/min	ISO 178	MPa	3000
Flexural Strength	2mm/min	ISO 178	MPa	125
Charpy Notched Impact Strength	+23°C	ISO 179/1 eA	KJ/m <sup>2</sup>	8
<b>Thermal Properties</b>				
Melting Temperature	10°C/min	ISO 11357-1-3	°C	260
Heat Deflection Temperature	1.8 MPa	ISO 75/2 A f	°C	85
Vicat Softening Temperature	50°C/h	ISO 306/B50 50N	°C	240
<b>Flammability Properties</b>				
Flammability	0.8mm	UL 94	class	HB
Glow Wire Flammability Index	2mm	IEC 60695-2-1/2	°C/mm	750
Automotive interior flammability	Burn rate	FMVSS302	mm/min	0
<b>Electrical Properties</b>				
Volume resistivity	500V	IEC 60093	ohm · m	1 E+13 1 E+11
Surface resistivity	500V	IEC 60093	ohm	1 E+12 1 E+10

\*DAM = Dry As Moulded state \*\*Cond = Conditioned state similar to ISO 1110 \*\*\*Melt Temp [°C] / Mold Temp [°C] / Cavity press [MPa]

