

# RADILON A ERV3808 100 NAT

Material code

Colour code

## DESCRIPTION

PA66 30% glass fiber reinforced injection moulding grade. Toughened. Natural colour.

Suitable for parts requiring improved impact strength along with high stiffness and mechanical reinforcement.

ISO 1043 : PA66-I GF30

## MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.15%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more.

Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

### Processing Parameters

Melt Temperature:	Mold Temperature:	Injection Speed:
280 ÷ 300 °C	80 ÷ 100 °C	Medium-high

## PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet

RoHS compliant 2002/95/CE and following amendments



## Technical data sheet

# RADILON A ERV3808 100 NAT

Material code      Colour code

PROPERTY	STANDARD	UNIT	VALUE	
			DAM*	Cond**
<b>Physical Properties</b>				
Density	ISO 1183	Kg/m <sup>3</sup>	1280	
Moisture absorption 23°C – 50%RH	2mm thk ISO 62	%	1.6	
Water absorption, immersion at 23°C	2mm thk ISO 62	%	5.6	
<b>Mechanical Properties</b>				
Tensile Modulus	1mm/min ISO 527-2/1A	MPa	8400	
Stress at Break	5mm/min ISO 527-2/1A	MPa	125	
Strain at Break	5mm/min ISO 527-2/1A	%	3	
Flexural Modulus	2mm/min ISO 178	MPa	7000	
Flexural Strength	2mm/min ISO 178	MPa	190	
Charpy Impact Strength	+23°C ISO 179/1 eU	KJ/m <sup>2</sup>	80	
Charpy Notched Impact Strength	+23°C ISO 179/1 eA	KJ/m <sup>2</sup>	18	
Charpy Notched Impact Strength	-30°C ISO 179/1 eA	KJ/m <sup>2</sup>	13	
<b>Thermal Properties</b>				
Melting Temperature	10°C/min ISO 11357-1-3	°C	260	
Heat Deflection Temperature	1.8 MPa ISO 75/2 A f	°C	225	
Heat Deflection Temperature	0.45 MPa ISO 75/2 B f	°C	240	
Vicat Softening Temperature	50°C/h ISO 306/B50 50N	°C	230	
<b>Flammability Properties</b>				
Flammability	0.8mm UL 94	class	HB	
Automotive interior flammability	Burn rate FMVSS302	mm/min	0	
<b>Electrical Properties</b>				
Volume resistivity	500V IEC 60093	ohm · m	1 E+13	1 E+11
Surface resistivity	500V IEC 60093	ohm	1 E+12	1 E+10
Comparative Tracking Index	Sol.A IEC 60112	V	600	

\*DAM = Dry As Moulded state \*\*Cond = Conditioned state similar to ISO 1110 \*\*\*Melt Temp [°C] / Mold Temp [°C] / Cavity press [MPa]

