

RADILON A RV200 100 NAT

Material code

Colour code

DESCRIPTION

PA66 20% glass fiber reinforced injection moulding grade. Natural colour.

Suitable for parts requiring improved stiffness.

ISO 1043 : PA66 GF20

MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.15%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more.

Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

Processing Parameters

Melt Temperature:	Mold Temperature:	Injection Speed:
280 ÷ 300 °C	80 ÷ 100 °C	Medium-high

PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet

RoHS compliant 2002/95/CE and following amendments





Technical data sheet

RADILON A RV200 100 NAT

Material code

Colour code

PROPERTY		STANDARD	UNIT	VALUE	
				DAM*	Cond**
Physical Properties					
Density		ISO 1183	Kg/m ³	1260	
Moisture absorption 23°C – 50%RH	2mm thk	ISO 62	%	2.1	
Water absorption, immersion at 23°C	2mm thk	ISO 62	%	7.8	
Mechanical Properties					
Tensile Modulus	1mm/min	ISO 527-2/1A	MPa	6900	4100
Stress at Break	5mm/min	ISO 527-2/1A	MPa	140	90
Strain at Break	5mm/min	ISO 527-2/1A	%	3	5
Flexural Modulus	2mm/min	ISO 178	MPa	6400	3450
Flexural Strength	2mm/min	ISO 178	MPa	215	125
Charpy Impact Strength	+23°C	ISO 179/1 eU	KJ/m ²	50	65
Charpy Impact Strength	-30°C	ISO 179/1 eU	KJ/m ²	45	
Charpy Notched Impact Strength	+23°C	ISO 179/1 eA	KJ/m ²	9.5	12
Charpy Notched Impact Strength	-30°C	ISO 179/1 eA	KJ/m ²	8	
Thermal Properties					
Melting Temperature	10°C/min	ISO 11357-1-3	°C	260	
Heat Deflection Temperature	1.8 MPa	ISO 75/2 A f	°C	220	
Heat Deflection Temperature	0.45 MPa	ISO 75/2 B f	°C	250	
Vicat Softening Temperature	50°C/h	ISO 306/B50 50N	°C	240	
Flammability Properties					
Flammability	0.8mm	UL 94	class	HB	
Glow Wire Flammability Index	2mm	IEC 60695-2-1/2	°C/mm	700	
Glow Wire Ignition Temperature	2mm	IEC 60695-2-1/3	°C/mm	725	
Automotive interior flammability	Burn rate	FMVSS302	mm/min	0	
Electrical Properties					
Volume resistivity	500V	IEC 60093	ohm · m	1 E+13	1 E+11
Surface resistivity	500V	IEC 60093	ohm	1 E+12	1 E+10
Comparative Tracking Index	Sol.A	IEC 60112	V	600	

*DAM = Dry As Moulded state **Cond = Conditioned state similar to ISO 1110 ***Melt Temp [°C] / Mold Temp [°C] / Cavity press [MPa]

