

# RADILON D 40EP25ZW 333 NER 6497

*Material code**Colour code*

PROVISIONAL

## DESCRIPTION

PA610 flexible, high viscosity extrusion grade. Toughened and plasticized. Heat stabilized. Black colour.

Suitable for extrusion of pipes, profiles and cable jackets. Good impact resistance also at low temperatures. This grade is partially renewably-sourced (60% of base polymer by weight).

ISO 1043 : PA610-HI-P

## MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.10%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more.

Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

### Processing Parameters

Melt Temperature:	Mold Temperature:	Injection Speed:	Extrusion Temp: 230 ÷ 250 °C
230 ÷ 260 °C	70 ÷ 80 °C	Medium	

## PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet

RoHS compliant 2002/95/CE and following amendments





## Technical data sheet

PROVISIONAL

# RADILON D 40EP25ZW 333 NER 6497

Material code

Colour code

PROPERTY	UNIT	STANDARD	VALUE	
			DAM*	Cond**
<b>Physical Properties</b>				
Density		ISO 1183	Kg/m <sup>3</sup>	1040
Moisture absorption 23°C – 50%RH	2mm thk	ISO 62	%	0,9
Water absorption, immersion at 23°C	2mm thk	ISO 62	%	2
<b>Mechanical Properties</b>				
Tensile Modulus	1mm/min	ISO 527-2/1A	MPa	580
Stress at 100% strain	50mm/min	ISO 527-2/1A	MPa	30
Stress at Break	5mm/min	ISO 527-2/1A	MPa	36
Nominal Strain at Break	50mm/min	ISO 527-2/1A	%	>100
Flexural Modulus	2mm/min	ISO 178	MPa	460
Flexural Strength	2mm/min	ISO 178	MPa	20
Charpy Notched Impact Strength	+23°C	ISO 179/1 eA	KJ/m <sup>2</sup>	85
<b>Thermal Properties</b>				
Melting Temperature	10°C/min	ISO 11357-1-3	°C	215
Heat Deflection Temperature	1.8 MPa	ISO 75/2 A f	°C	50
Heat Deflection Temperature	0.45 MPa	ISO 75/2 B f	°C	100
<b>Electrical Properties</b>				
Volume resistivity	500V	IEC 60093	ohm · m	1 E+13 1 E+11
Surface resistivity	500V	IEC 60093	ohm	1 E+12 1 E+10

\*DAM = Dry As Moulded state \*\*Cond = Conditioned state similar to ISO 1110 \*\*\*Melt Temp [°C] / Mold Temp [°C] / Cavity press [MPa]

