

RADILON D 40P50K 333 NER 5624

Material code Colour code

PROVISIONAL

DESCRIPTION

PA610 flexible, high viscosity extrusion grade. Plasticized. Heat stabilized. Black colour.

Suitable for extrusion of tubes and profiles. Typical application: air pressure pipes.
This grade is partially renewably-sourced (60% of base polymer by weight).

ISO 1043 : PA610-P

MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.10%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more.

Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

Processing Parameters

Melt Temperature:	Mold Temperature:	Injection Speed:	Extrusion Temp: 230 ÷ 250 °C
230 ÷ 260 °C	70 ÷ 80 °C	Medium	

PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet

RoHS compliant 2002/95/CE and following amendments





Technical data sheet

PROVISIONAL

RADILON D 40P50K 333 NER 5624

Material code

Colour code

PROPERTY	STANDARD	UNIT	VALUE	
			DAM*	Cond**
Physical Properties				
Density	ISO 1183	Kg/m ³	1095	
Moisture absorption 23°C – 50%RH	2mm thk ISO 62	%	1.1	
Water absorption, immersion at 23°C	2mm thk ISO 62	%	2.5	
Mechanical Properties				
Tensile Modulus	1mm/min ISO 527-2/1A	MPa	900	550
Stress at Yield	50mm/min ISO 527-2/1A	MPa	39	30
Yield Strain	50mm/min ISO 527-2/1A	%	40	
Stress at Break	5mm/min ISO 527-2/1A	MPa	49	
Nominal Strain at Break	50mm/min ISO 527-2/1A	%	300	>100
Flexural Modulus	2mm/min ISO 178	MPa	710	
Flexural Strength	2mm/min ISO 178	MPa	29	
Charpy Notched Impact Strength	+23°C ISO 179/1 eA	KJ/m ²	15	25
Charpy Notched Impact Strength	-30°C ISO 179/1 eA	KJ/m ²	5	
Thermal Properties				
Melting Temperature	10°C/min ISO 11357-1-3	°C	215	
Heat Deflection Temperature	1.8 MPa ISO 75/2 A f	°C	50	

The characteristics shown here must be considered purely provisional and indicative for a product at developmental stage.

*DAM = Dry As Moulded state **Cond = Conditioned state similar to ISO 1110 ***Melt Temp [°C] / Mold Temp [°C] / Cavity press [MPa]

