

# RADILON DT 40EP75W 333 NER 7623

Material code

Colour code

PROVISIONAL

## DESCRIPTION

PA612 semi-rigid, high viscosity extrusion grade. Toughened. Heat stabilized. Black colour.

Suitable for extrusion of profiles, tubes and pipes.

ISO 1043 : PA612-I-P

## MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.10%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more.

Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

### Processing Parameters

Melt Temperature:	Mold Temperature:	Injection Speed:	Extrusion Temp: 230 ÷ 250 °C
230 ÷ 260 °C	70 ÷ 80 °C	Medium	

## PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet

RoHS compliant 2011/65/UE and following amendments





# Technical data sheet

PROVISIONAL

## RADILON DT 40EP75W 333 NER 7623

Material code

Colour code

PROPERTY		STANDARD	UNIT	VALUE	
				DAM*	Cond**
<b>Physical Properties</b>					
Density		ISO 1183	Kg/m <sup>3</sup>	1048	
Moisture absorption 23°C – 50%RH	2mm thk	ISO 62	%	1.1	
Water absorption, immersion at 23°C	2mm thk	ISO 62	%	2.7	
<b>Mechanical Properties</b>					
Tensile Modulus	1mm/min	ISO 527-2/1A	MPa	1380	880
Stress at Yield	50mm/min	ISO 527-2/1A	MPa	44	34
Yield Strain	50mm/min	ISO 527-2/1A	%	18	24
Stress at Break	5mm/min	ISO 527-2/1A	MPa	49	45
Nominal Strain at Break	50mm/min	ISO 527-2/1A	%	>300	>300
Flexural Modulus	2mm/min	ISO 178	MPa	1150	790
Flexural Strength	2mm/min	ISO 178	MPa	45	30
Charpy Notched Impact Strength	+23°C	ISO 179/1 eA	KJ/m <sup>2</sup>	45	95
Charpy Notched Impact Strength	-30°C	ISO 179/1 eA	KJ/m <sup>2</sup>	13	14
<b>Thermal Properties</b>					
Melting Temperature	10°C/min	ISO 11357-1-3	°C	210	
Heat Deflection Temperature	1.8 MPa	ISO 75/2 A f	°C	50	
<b>Electrical Properties</b>					
Volume resistivity	500V	IEC 60093	ohm · m	1 E+13	1 E+11
Surface resistivity	500V	IEC 60093	ohm	1 E+12	1 E+10

The characteristics shown here must be considered purely provisional and indicative for a product at developmental stage.

\*DAM = Dry As Moulded state \*\*Cond = Conditioned state similar to ISO 1110 \*\*\*Melt Temp [°C] / Mold Temp [°C] / Cavity press [MPa]

