

# RADILON S BMV150K 333 NER 2578

Material code      Colour code

PROVISIONAL

## DESCRIPTION

PA6 15% glass fiber reinforced, high viscosity blow moulding grade. Toughened, heat stabilized. Black colour.

Suitable for blow-moulding of tubes and containers; typically used for automotive air pipes, including turbo air ducts.

ISO 1043 : PA6-T GF15

## MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.15%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more.

Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

### Processing Parameters

Melt Temperature:	Mold Temperature:	Injection Speed:	Extrusion Temp: 250 ÷ 280 °C
250 ÷ 280 °C	70 ÷ 80 °C	Medium	

## PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet

RoHS compliant 2002/95/CE and following amendments





# Technical data sheet

PROVISIONAL

## RADILON S BMV150K 333 NER 2578

Material code      Colour code

PROPERTY	STANDARD	UNIT	VALUE	
			DAM*	Cond**
<b>Physical Properties</b>				
Density	ISO 1183	Kg/m <sup>3</sup>	1200	
Melt Flow Index	ISO 1133	g/10'	5	
			275°C / 5kg	
<b>Mechanical Properties</b>				
Tensile Modulus	ISO 527-2/1A	MPa	5200	
Stress at Break	ISO 527-2/1A	MPa	95	
Strain at Break	ISO 527-2/1A	%	3.8	
Flexural Modulus	ISO 178	MPa	4000	
Flexural Strength	ISO 178	MPa	135	
Charpy Impact Strength	ISO 179/1 eU	KJ/m <sup>2</sup>	65	
Charpy Notched Impact Strength	ISO 179/1 eA	KJ/m <sup>2</sup>	10	
Charpy Notched Impact Strength	ISO 179/1 eA	KJ/m <sup>2</sup>	6	
			+23°C	
			+23°C	
			-30°C	
<b>Thermal Properties</b>				
Melting Temperature	ISO 11357-1-3	°C	220	
Heat Deflection Temperature	ISO 75/2 A f	°C	140	
			10°C/min	
			1.8 MPa	
<b>Flammability Properties</b>				
Flammability	UL 94	class	HB	
Automotive interior flammability	FMVSS302	mm/min	0	
			0.8mm	
			Burn rate	
<b>Electrical Properties</b>				
Volume resistivity	IEC 60093	ohm · m	1 E+13	1 E+11
Surface resistivity	IEC 60093	ohm	1 E+12	1 E+10
			500V	
			500V	

\*DAM = Dry As Moulded state \*\*Cond = Conditioned state similar to ISO 1110 \*\*\*Melt Temp [°C] / Mold Temp [°C] / Cavity press [MPa]

