

Ryton® R-4-240BL

polyphenylene sulfide

Ryton® R-4-240NA and R-4-240BL 40% glass fiber reinforced polyphenylene sulfide compounds provide enhanced mechanical strength and

toughness compared to other polyphenylene sulfide compounds.

General

Material Status	• Commercial: Active	
Availability	• Asia Pacific • Europe	• Latin America • North America
Filler / Reinforcement	• Glass Fiber, 40% Filler by Weight	
Features	• Good Strength	• Good Toughness
Uses	• Automotive Under the Hood	
RoHS Compliance	• RoHS Compliant	
Appearance	• Black	
Forms	• Pellets	
Processing Method	• Injection Molding	

Physical	Typical Value	Unit	Test method
Density / Specific Gravity	1.66		ASTM D792
Molding Shrinkage			
Flow : 3.20 mm	0.20	%	
Across Flow : 3.20 mm	0.50	%	
Water Absorption (24 hr, 23°C)	0.020	%	ASTM D570

Mechanical	Typical Value	Unit	Test method
Tensile Strength			
--	165	MPa	ASTM D638
--	175	MPa	ISO 527-2
Tensile Elongation (Break)	1.7	%	ASTM D638 ISO 527-2
Flexural Modulus			
--	13800	MPa	ASTM D790
--	14000	MPa	ISO 178
Flexural Strength			
--	248	MPa	ASTM D790
--	255	MPa	ISO 178
Compressive Strength	265	MPa	ASTM D695
Poisson's Ratio	0.39		ISO 527



Ryton® R-4-240BL

polyphenylene sulfide

Impact	Typical Value	Unit	Test method
Notched Izod Impact			
3.18 mm	85	J/m	ASTM D256
--	9.0	kJ/m ²	ISO 180/A
Unnotched Izod Impact			
3.18 mm	640	J/m	ASTM D4812
--	40	kJ/m ²	ISO 180

Hardness	Typical Value	Unit	Test method
Rockwell Hardness			ASTM D785
M-Scale	99		
R-Scale	120		

Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed	265	°C	
CLTE			ASTM E831
Flow : -50 to 50°C	2.0E-5	cm/cm/°C	
Flow : 100 to 200°C	1.5E-5	cm/cm/°C	
Transverse : -50 to 50°C	4.0E-5	cm/cm/°C	
Transverse : 100 to 200°C	9.0E-5	cm/cm/°C	
Thermal Conductivity	0.31	W/m/k	
UL Temperature Rating	200 to 220	°C	UL 746B

Electrical	Typical Value	Unit	Test method
Surface Resistivity	1.0E+16	ohms	ASTM D257
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength	22	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
25°C, 1 kHz	3.90		
25°C, 1 MHz	4.00		
Dissipation Factor			ASTM D150
25°C, 1 kHz	2.0E-3		
25°C, 1 MHz	2.0E-3		
Arc Resistance	130	sec	ASTM D495
Comparative Tracking Index (CTI)	175	V	IEC 60112
Comparative Tracking Index (CTI)	PLC 4		UL 746A
Insulation Resistance ¹ (90°C)	1.0E+12	ohms	

Flammability	Typical Value	Unit	Test method
Flame Rating (1.6 mm)	V-0		UL 94
	5VA		
Oxygen Index	54	%	ASTM D2863



Ryton® R-4-240BL

polyphenylene sulfide

Injection	Typical Value	Unit
Drying Temperature	135 to 150	°C
Drying Time	2.0 to 4.0	hr
Rear Temperature	295 to 315	°C
Middle Temperature	305 to 325	°C
Front Temperature	315 to 345	°C
Nozzle Temperature	305 to 325	°C
Processing (Melt) Temp	320 to 330	°C
Mold Temperature	135 to 150	°C

Notes

Typical properties: these are not to be construed as specifications.

¹ 95%RH, 48 hr

