

# Ryton® R-7-190BL

## polyphenylene sulfide

Ryton® R-7-190BL glass fiber and mineral filled polyphenylene sulfide compound provides

enhanced strength and low maintenance molding using conventional molding equipment.

### General

Material Status	• Commercial: Active	
Availability	• Asia Pacific • Europe	• Latin America • North America
Filler / Reinforcement	• Glass Fiber \ Mineral	
Features	• Chemical Resistant • Good Electrical Properties	• Good Strength
RoHS Compliance	• RoHS Compliant	
Appearance	• Black	
Forms	• Pellets	

### Physical

	Typical Value	Unit	Test method
Density <sup>1</sup>	2.00	g/cm <sup>3</sup>	ISO 1183
Water Absorption (24 hr, 23°C)	0.020	%	ASTM D570
Mold Shrinkage <sup>2</sup>			
Flow	0.20	%	
Transverse	0.40	%	

### Mechanical

	Typical Value	Unit	Test method
Tensile Strength	140	MPa	ISO 527
Tensile Elongation (Break)	1.0	%	ISO 527
Flexural Modulus	18000	MPa	ISO 178
Flexural Strength	220	MPa	ISO 178
Compressive Strength	275	MPa	ISO 604

### Impact

	Typical Value	Unit	Test method
Charpy Notched Impact Strength	7.0	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength	22	kJ/m <sup>2</sup>	ISO 179/1eU
Notched Izod Impact Strength	7.0	kJ/m <sup>2</sup>	ISO 180/A
Unnotched Izod Impact Strength	20	kJ/m <sup>2</sup>	ISO 180



# Ryton® R-7-190BL

## polyphenylene sulfide

Thermal	Typical Value	Unit	Test method
CLTE			ISO 11359-2
Flow : -50 to 50°C	1.5E-5	cm/cm/°C	
Flow : 100 to 200°C	1.5E-5	cm/cm/°C	
Transverse : -50 to 50°C	2.5E-5	cm/cm/°C	
Transverse : 100 to 200°C	6.5E-5	cm/cm/°C	
Thermal Conductivity	0.64	W/m/K	ASTM E1530
Heat Deflection Temperature - 1.8 MPa	265	°C	ASTM D648
Temperature Index	220 to 240	°C	UL 746B

Electrical	Typical Value	Unit	Test method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength	18	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
25°C, 1 kHz	5.20		
25°C, 1 MHz	5.00		
Dissipation Factor			ASTM D150
25°C, 1 kHz	2.0E-3		
25°C, 1 MHz	2.0E-3		
Arc Resistance	185	sec	ASTM D495
Comparative Tracking Index (CTI)	250	V	IEC 60112
Comparative Tracking Index (CTI)	PLC 2		UL 746A
Insulation Resistance - 95% RH, 48 hr (90°C)	1.00E+13	ohms	

Flammability	Typical Value	Unit	Test method
Flame Rating (1.6 mm)	V-0		UL 94
	5VA		

### Additional Information

Test specimen molding conditions: Stock temperature, 315-345°C; Mold temperature, 135°C

Injection	Typical Value	Unit
Drying Temperature	135 to 150	°C
Drying Time	2.0 to 4.0	hr
Rear Temperature	295 to 315	°C
Middle Temperature	305 to 325	°C
Front Temperature	315 to 345	°C
Nozzle Temperature	305 to 325	°C
Processing (Melt) Temp	320 to 330	°C
Mold Temperature	135 to 150	°C

## Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Method A

<sup>2</sup> Measured on 102 mm x 102 mm x 3.2 mm plaques, edge gated.

