

Tecnoflon® PFR 95HT

perfluoroelastomer

Tecnoflon® PFR 95HT is a perfluoroelastomer (FFKM) offering a significantly wider operational range and superior compression set resistance than any other perfluoroelastomer, thanks to its unique peroxide curing system that does not need any coagent (TAIC or equivalent) for curing to be carried out. It can offer a very broad chemical resistance in a wide variety of media including acids, caustics, ketones, aldehydes, esters, ethers, methanol, solvents, sour gases, hydrocarbons, steam, hot water and mixed process streams along with excellent thermal resistance.

Tecnoflon® PFR 95HT is suitable for most applications in temperature ranging from -10°C to 300°C.

Tecnoflon® PFR 95HT can be combined with other typical fluoroelastomer compounding ingredients; its mixing can be accomplished with two-roll mills or internal mixers. Finished goods may be produced by a variety of rubber processing methods.

The primary use for Tecnoflon® PFR 95HT is the manufacturing of any kind of elastomeric sealing

element such as O-rings, gaskets, valve bodies, butterfly valves, pump housings and stators, metal bonded parts, diaphragms, profiles, etc. These sealing elements can be used in mechanical seals, pumps, compressors, valves, reactors, mixers, sprayers, dispensers, quick connect couplings, controls, instrumentation, etc. in chemical and petrochemical industry, hydrocarbon processing, petroleum exploration and extraction, bio-analytical industry, aerospace and semiconductor manufacturing industries.

Tecnoflon® PFR 95HT is marketed in the form of raw polymer (1 kg and 5 kg boxes) in order to give the transformer the freedom and the opportunity to develop and fine-tune compounds and items best suited to produce high performance rubber articles such as O-rings, seals, diaphragms and other parts used in process industries.

General

Material Status	• Commercial: Active	
Availability	• Europe	• North America
Features	• Acid Resistant • Alcohol Resistant • Chemical Resistant • Fuel Resistant • High Heat Resistance	• Low Compression Set • Moisture Resistant • Solvent Resistant • Steam Resistant
Uses	• Blending • Compounding • Diaphragms • Gaskets	• Profiles • Pump Parts • Seals • Valves/Valve Parts
Appearance	• Translucent	
Forms	• Slab	
Processing Method	• Compounding	

Physical

Typical Value Unit

Mooney Viscosity ¹ (ML 1+10, 121°C)	75 MU
--	-------

Notes

Typical properties: these are not to be construed as specifications.

¹ Raw polymer

