

TORZEN G3301HSL BK20

Material Code

Colour Code

DESCRIPTION

PA66 33% glass fiber reinforced injection moulding grade. Heat stabilized. Black colour.

Suitable for parts requiring high stiffness, good mechanical resistance and good heat ageing properties retention.

ISO 1043 : PA66-T GF33

MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.15%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more.

Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

Processing Parameters

Melt Temperature:	Mold Temperature:	Injection Speed:
280 ÷ 300 °C	80 ÷ 100 °C	Medium-high

PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet

RoHS compliant 2011/65/UE and following amendments



TECHNICAL DATA SHEET

TORZEN G3301HSL BK20

Material Code

Colour Code

PROPERTY		STANDARD	UNIT	VALUE	
				DAM*	Cond**
Physical Properties					
Density		ISO 1183	Kg/m ³	1410	
Moulding shrinkage – Parallel / Normal		ISO 294-4	%	0,2-0,4 / 0,9-1,1	
Moisture absorption 23°C – 50%RH	2mm thk	ISO 62	%	1,8	
Water absorption, 24h immersion at 23°C	2mm thk	ISO 62	%	1,2	
Mechanical Properties					
Tensile Modulus	1mm/min	ISO 527-2/1A	MPa	10100	
Stress at Break	5mm/min	ISO 527-2/1A	MPa	170	
Strain at Break	5mm/min	ISO 527-2/1A	%	2,4	
Flexural Modulus	2mm/min	ISO 178	MPa	9100	
Flexural Strength	2mm/min	ISO 178	MPa	255	
Charpy Notched Impact Strength	+23°C	ISO 179/1 eA	kJ/m ²	7	
Charpy Notched Impact Strength	-40°C	ISO 179/1 eA	kJ/m ²	6	
Izod Notched Impact Strength	+23°C	ISO 180/1 eA	kJ/m ²	7	
Thermal Properties					
Melting Temperature	10°C/min	ISO 11357-1-3	°C	262	
Heat Deflection Temperature	1.8 MPa	ISO 75/2 A f	°C	245	
Heat Deflection Temperature	0.45 MPa	ISO 75/2 B f	°C	258	

*DAM = Dry As Moulded state **Cond = Conditioned state similar to ISO 1110 ***Melt Temp [°C] / Mold Temp [°C] / Cavity press [MPa]

