

Tecnoflon® P 959 fluoroelastomer

TECNOFLON® P 959 is a medium viscosity, high fluorine (70%), peroxide curable fluoroelastomer. Tecnoflon® P 959 exhibits superior resistance to a wide variety of chemicals, coupled with excellent processability and optimum compression set. Tecnoflon® P 959 can be cross-linked using organic peroxides in conjunction with a co-agent.

Some of the basic properties of TECNOFLON® P 959 are:

- Low post cure
- Superior mold flow
- Lack of mold fouling
- Excellent mold release
- Good chemical resistance especially in:
 - Alcohol containing fuels

- Steam
- Fluids containing amine additives

Tecnoflon® P 959 can be used for compression, injection and transfer molding of shaft seals, valve seals, O-rings, gaskets or any item requiring superior chemical resistance.

Tecnoflon® P 959 can be combined with the cure system and other typical fluoroelastomer compounding ingredients. Mixing can be accomplished with two-roll mills or internal mixers. Finished goods may be produced by a variety of rubber processing methods. This material can be extruded into hoses or profiles and can be calendered to make sheet stocks or belting.

General

Material Status	• Commercial: Active	
Availability	• Europe	• North America
Features	<ul style="list-style-type: none"> • Alcohol Resistant • Chemical Resistant • Crosslinkable • Fuel Resistant • Good Flow 	<ul style="list-style-type: none"> • Good Mold Release • Good Processability • Low Compression Set • Medium Viscosity • Steam Resistant
Uses	<ul style="list-style-type: none"> • Belts/Belt Repair • Blending • Gaskets • Hose 	<ul style="list-style-type: none"> • Profiles • Seals • Sheet • Valves/Valve Parts
Appearance	• Translucent	
Forms	• Slab	
Processing Method	<ul style="list-style-type: none"> • Calendering • Compounding • Compression Molding 	<ul style="list-style-type: none"> • Extrusion • Injection Molding • Transfer Molding

Physical

	Typical Value	Unit
Mooney Viscosity ¹ (ML 1+10, 121°C)	48	MU
Fluorine Content ¹	70	%

Notes

Typical properties: these are not to be construed as specifications.

¹ Raw polymer

