

Tribocomp® PA66 LGF30 TS0 S8 polyamide 66

Tribocomp® PA66 LGF30 TS0 S8, is a 30% long glass fiber reinforced, black, high-flow PA66 compound containing 15% PTFE and having excellent

tribological performance. It can easily be processed on most injection molding machines.

General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Filler / Reinforcement	• Long Glass Fiber, 30% Filler by Weight	• PTFE, 15% Filler by Weight
Features	• Abrasion Resistant • Heat Stabilized • High Flow	• High Friction • High Temperature Strength • Low Shrinkage
Uses	• Automotive Applications • Automotive Under the Hood • Engineering Parts	• Gears • Industrial Applications • Power/Other Tools
RoHS Compliance	• RoHS Compliant	
Appearance	• Black	
Forms	• Pellets	
Processing Method	• Compression Molding	• Injection Molding

Physical	Dry	Conditioned	Unit	Test method
Density	1.50	--	g/cm ³	ISO 1183
Molding Shrinkage - Flow	0.40	--	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	1.4	--	%	ISO 62

Mechanical	Dry	Conditioned	Unit	Test method
Tensile Modulus				ISO 527-1
23°C	10500	8000	MPa	
90°C	6600	--	MPa	
Tensile Stress				ISO 527-2
Break, 23°C	195	145	MPa	
Break, 90°C	125	--	MPa	
Tensile Strain				ISO 527-2
Yield, 23°C	3.0	--	%	
Break, 23°C	--	2.0	%	
Flexural Modulus (23°C)	10200	--	MPa	ISO 178
Flexural Stress (23°C)	285	--	MPa	ISO 178



Tribocomp® PA66 LGF30 TS0 S8 polyamide 66

Mechanical	Dry	Conditioned	Unit	Test method
Coefficient of Friction				ASTM D3702
Dynamic	0.23	--		
Static	0.18	--		
Wear Factor	13.0	--		ASTM D3702

Impact	Dry	Conditioned	Unit	Test method
Charpy Notched Impact Strength (23°C)	20	--	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	70	--	kJ/m ²	ISO 179

Thermal	Dry	Conditioned	Unit	Test method
Deflection Temperature Under Load				
0.45 MPa, Unannealed	262	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	258	--	°C	ISO 75-2/A
Thermal Conductivity	0.29	--	W/m/K	ISO 22007
Coefficient of Linear Thermal Expansion	2.9E-5	--	cm/cm/°C	ISO 11359-2

Electrical	Dry	Conditioned	Unit	Test method
Electric Strength (2.00 mm)	35	--	kV/mm	IEC 60243-1
Comparative Tracking Index	500	--	V	IEC 60112
Surface Resistivity	1.0E+12	--	ohms/sq	ASTM D257

Additional Information

Dry The value listed as Molding Shrinkage ISO 294-4, was tested in accordance with S.O.P. methods.

Injection	Dry Unit
Drying Temperature	80 to 100 °C
Drying Time	4.0 hr
Suggested Max Moisture	0.10 %
Rear Temperature	290 to 300 °C
Middle Temperature	300 °C
Front Temperature	300 °C
Nozzle Temperature	300 °C
Processing (Melt) Temp	< 300 °C
Mold Temperature	80 to 120 °C

Injection Notes

Pre-drying -- Since polyamides are hygroscopic materials as well as sensitive to moisture during processing, this product should always be pre-dried.

Regrind -- Regrind of highly filled thermoplastic materials, such as this material, should only be recycled with special care. The regrind content must never exceed 15%, and only regrind of optimum quality should be used. In any case, part properties should be checked.

Notes

Typical properties: these are not to be construed as specifications.

