

LOTADER[®] 9307YT

LOTADER[®] 9307YT is a random ethylene-vinyl acetate-maleic anhydride terpolymer (EVA-MAH).

- As an ethylene copolymer, LOTADER[®] 9307YT is compatible with PE in all proportions, and with most ethylene copolymers.
- Vinyl acetate brings softness, flexibility, and polarity while maleic anhydride brings reactivity, leading to versatile adhesive properties to polar and non-polar substrates.
- As a result of high-pressure polymerization in tubular reactor, LOTADER[®] 9307YT also exhibits high transparency (low haze).

LOTADER[®] 9307YT is suitable to produce thermo-adhesive films for solid substrates like PA, PET & PU films, aluminum foils, fiber mats, foams... OREVAC[®] T 9307 Y can also be used as a skin packaging adhesive on all type of cardboard.

Typical Properties

	Test Method	Unit	Typical value
Vinyl Acetate content	FTIR (Internal Method)	% wt.	14
Maleic Anhydride content	FTIR (internal method)	ppm	1600
Melt Index (190°C / 2.16 kg)	ISO 1133 / ASTM D1238	g/10min	10.5
Melting point	ISO 11357-3	°C	93
Density	ISO 1183 / ASTM D1505	g/cm ³	0.94
Vicat softening temperature (10N) ⁽¹⁾	ISO 306 / ASTM D1525	°C	66
Ring & Ball temperature	ASTM E28	MPa	145
Elongation at break ⁽¹⁾	ISO 527-2 / ASTM D638	%	800
Tensile strength at break ⁽¹⁾	ISO 527-2 / ASTM D638	MPa	19
Hardness Shore A ⁽¹⁾	ISO 868 / ASTM D2240		91

¹: On compression molded samples.



Processing

LOTADER® 9307YT can be processed on most conventional equipment used for thermoplastics. It is recommended to avoid overheating above 230°C and to purge the equipment after a run is completed.

Storage, Handling & Safety

LOTADER® 9307YT should be stored in dry conditions protected from UV-light. Improper storage conditions may cause degradation and have consequences on physical properties of the product.

