

LOTRYL[®] 35BA40T

LOTRYL[®] 35BA40T is a random ethylene-butyl acrylate copolymer.

- Due to the high butyl acrylate content, LOTRYL[®] 35BA40T can be used for applications where flexibility and polarity are required.
- Thanks to its high fluidity, LOTRYL[®] 35BA40T is suitable for the formulation of hot melt adhesives. It can also be used in polyesters as an impact modifier for high fluidity compounds

Typical Properties

	Test Method	Unit	Typical Value
Butyl Acrylate Content	FTIR (internal method)	%.-wt.	35
Melt Index (190°C/2.16kg)	ISO 1133 / ASTM D1238	g/10min.	40
Melting Point	ISO 11357-3	°C	89
Density	ISO 1193 / ASTM D150	g/cm ³	0.94
Vicat Softening Temperature (10N) ¹	ISO 306 / ASTM D1525	°C	<40
Ring & Ball Temperature	ASTM E28	°C	134
Flexural Modulus ¹	ISO 178 / ASTM D790	MPa	<10
Elongation at Break ¹	ISO 527-2 / ASTM D638	%	400
Tensile Strength at Break ¹	ISO 527-2 / ASTM D638	MPa	1.8
Hardness Shore A ¹	ISO 868 / ASTM D2240		60

¹: On compression molded samples.



Processing

LOTRYL® 35BA40T can be processed with standard polyolefin extrusion equipment up to 300°C and it is recommended to purge the equipment after a run is completed.

If LOTRYL® 35BA40T is used pure for instance with blown or cast film technology, standard temperature settings could be:

Zone 1	Zone 2	Zone 3	Zone 4	Fittings-Channels	Die
150 - 170°C	170°C	170°C	170°C	170°C	170°C

Final profile and settings depend on the line and multilayer structure being run.

Storage, Handling & Safety

LOTRYL® 35BA40T should be stored in standard conditions and protected from UV-light. Improper storage conditions may cause degradation and could have consequences on physical properties of the product.

Due to its physical properties, it may be possible that the LOTRYL® 35BA40T shows some caking. This is particularly true during summer time.

