

# OREVAC<sup>®</sup> 18790

OREVAC<sup>®</sup> 18790 is a maleic anhydride modified polypropylene. It is available in pellet form for use in conventional extrusion and coextrusion equipment designed to process polyolefin.

## Typical Properties

	Test Method	Unit	Typical Value
Melt Index (190°C/ 325 g)	ISO 1133 / ASTM D1238	g/10min.	45
Melting Point	ISO 11357-3	°C	137
Density	ISO 1183 / ASTM D1505	g/cm <sup>3</sup>	0.90
Vicat softening temperature (10N)	ISO 306 / ASTM D1525	°C	115

## Processing

OREVAC<sup>®</sup> 18790 must be used as concentrate and blended with other polyolefin under conditions typically used in extrusion of polypropylene resins.

This material is not corrosive and is readily processed with standard polyolefin equipment.

For any processing advice, please refer to our technical services.

## Storage, Handling & Safety

OREVAC<sup>®</sup> 18790 should be stored in dry conditions protected from UV-light. Improper storage conditions may cause degradation and have consequences on physical properties of the product.

