



Titacon GF910

RESIN : POLYACETAL RESIN

PRODUCT DESCRIPTION : 10%GLASS FIBER REINFORCED, HIGH
STRENGTH/STIFFNESS, DIMENSIONAL ACCURACY.

Properties	Unit	method	Value
Color	-	-	Natural
specific gravity	g/cm ³	ISO 1183	1.48
Tensile strength	MPa	ISO	85
Tensile Elongation		527-1,2	>3.0
Flexural strength	MPa	ISO 178	125
Flexural modulus			4800
Charpy impact strength(notched)	kJ/m ²	ISO	6
		179/1eA	
Heat Deflection Temperature(1.8MPa)	°C	ISO 75-1,2	130
Volume resistivity	Ω•cm	IEC 60093	1×10 ¹⁴
Surface resistivity	Ω		1×10 ¹⁴
Flammability		UL 94	HB
Mold shrinkage	%	50x70x3 mmt	0.9~1.5
MOLDING CONDITION	°C	Drying	100x 3Hrs
		Melt Temp.	170~200
	%	Mold Temp.	60~100
		Inject. Press.	30~70
		Inject. Velocity	20~50

*All property values shown in this data sheet are the representative values and not minimum value of this material.

