



Titalon 1100GF

RESIN : POLYAMIDE6 RESIN

PRODUCT DESCRIPTION : 10%GLASS FIBER

Properties	Unit	method	Value
Color	-	-	Nature
specific gravity	g/cm ³	ISO 1183	1.20
Tensile strength	MPa	ISO	100
Tensile Elongation		527-1,2	>3
Flexural strength	MPa	ISO 178	140
Flexural modulus			4100
Charpy impact strength(notched)	kJ/m ²	ISO	7
		179/1eA	
Heat Deflection Temperature(1.8MPa)	°C	ISO 75-1,2	170
Volume resistivity	Ω•cm	IEC 60093	1×10 ¹⁴
Surface resistivity	Ω		1×10 ¹⁴
Flammability		UL 94	HB
Mold shrinkage	%	50x70x3 mmt	0.5~0.8
MOLDING CONDITION	°C	Drying	80~100x 4Hrs
		Melt Temp.	230~260
		Mold Temp.	60~100
	%	Inject. Press.	30~70
		Inject. Velocity	30~60

*All property values shown in this data sheet are the representative values and not minimum value of this material.

