



# Titalon 1300GB

RESIN : POLYAMIDE6 RESIN

PRODUCT DESCRIPTION : 30%GLASS BEADS FILLED,ANTI-SCRATCH

Properties	Unit	method	Value
Color	-	-	Nature
specific gravity	g/cm <sup>3</sup>	ISO 1183	1.36
Tensile strength	MPa	ISO	75
Tensile Elongation		527-1,2	>10
Flexural strength	MPa	ISO 178	100
Flexural modulus			3800
Charpy impact strength(notched)	kJ/m <sup>2</sup>	ISO	4
		179/1eA	
Heat Deflection Temperature(1.8MPa)	°C	ISO 75-1,2	100
Volume resistivity	Ω•cm	IEC 60093	1×10 <sup>14</sup>
Surface resistivity	Ω		1×10 <sup>14</sup>
Flammability		UL 94	HB
Mold shrinkage	%	50x70x3 mmt	1.2~1.6
MOLDING CONDITION			
	°C	Drying	80~100x 4Hrs
		Melt Temp.	230~260
		Mold Temp.	60~100
	%	Inject. Press.	30~70
		Inject. Velocity	30~60

\*All property values shown in this data sheet are the representative values and not minimum value of this material.

