



Titalon 1300GF

RESIN : POLYAMIDE6 RESIN

PRODUCT DESCRIPTION : 30% GLASS FIBER REINFORCED , HIGH STRENGTH.

Properties	Unit	method	Value
Color	-	-	Natural
specific gravity	g/cm ³	ISO 1183	1.38
Tensile strength	MPa	ISO	170
Tensile Elongation		527-1,2	>2
Flexural strength	MPa	ISO 178	260
Flexural modulus			9000
Charpy impact strength(notched)	kJ/m ²	ISO	14
		179/1eA	
Heat Deflection Temperature (1.8MPa)	°C	ISO 75-1,2	204
Volume resistivity	Ω•cm	IEC 60093	1×10 ¹³
Surface resistivity	Ω		1×10 ¹⁴
Flammability		UL 94	HB
Mold shrinkage	%	50x70x3 mmt	0.2~0.6
MOLDING CONDITION			
	°C	Drying	80~100x 4Hrs
		Melt Temperature	230~260
		Mold Temperature	60~100
	%	Inject. Pressure	30~70
		Inject. Velocity	30~60

*All property values shown in this data sheet are the representative values and not minimum value of this material.

