



Titalon 4015TF

RESIN : POLYAMIDE46 RESIN

PRODUCT DESCRIPTION : 15%PTFE FILLED, WEAR RESISTANCE

Properties	Unit	method	Value
Color	-	-	Natural
specific gravity	g/cm ³	ISO 1183	1.25
Tensile strength	MPa	ISO	75
Tensile Elongation		527-1,2	>7
Flexural strength	MPa	ISO 178	110
Flexural modulus			3100
Charpy impact strength(notched)	kJ/m ²	ISO 179/1eA	7
Heat Deflection Temperature (1.8MPa)	°C	ISO 75-1,2	180
Volume resistivity	Ω•cm	IEC 60093	1×10 ¹²
Surface resistivity	Ω		1×10 ¹²
Flammability		UL 94	HB
Mold shrinkage	%	50x70x3 mmt	1.2~2.0
MOLDING CONDITION	°C	Drying	100x 4Hrs
		Melt Temperature	290~320
		Mold Temperature	80~120
	%	Inject. Pressure	30~70
		Inject. Velocity	30~60

*All property values shown in this data sheet are the representative values and not minimum value of this material.

