



# Titalon 4150CTF

RESIN : POLYAMIDE46 RESIN

PRODUCT DESCRIPTION : 15% Carbon fiber 、PTFE filled, Wear resistance

Properties	Unit	method	Value
Color	-	-	Black
specific gravity	g/cm <sup>3</sup>	ISO 1183	1.24
Tensile strength	MPa	ISO	180
Tensile Elongation		527-1,2	>3
Flexural strength	MPa	ISO 178	250
Flexural modulus			9500
Charpy impact strength(notched)	kJ/m <sup>2</sup>	ISO	5
		179/1eA	
Heat Deflection Temperature (1.8MPa)	°C	ISO 75-1,2	280
Volume resistivity	Ω•cm	IEC 60093	1×10 <sup>4-5</sup>
Surface resistivity	Ω		1×10 <sup>4-5</sup>
Flammability		UL 94	HB
Mold shrinkage	%	50x70x3 mmt	0.4~1.0
MOLDING CONDITION	°C	Drying	100x 4Hrs
		Melt Temperature	290~320
		Mold Temperature	80~120
	%	Inject. Pressure	30~70
		Inject. Velocity	30~60

\*All property values shown in this data sheet are the representative values and not minimum value of this material.

