



Titalon 4300CF

RESIN : POLYAMIDE46 RESIN

PRODUCT DESCRIPTION : 30%CARBON FIBER REINFORCED

Properties	Unit	method	Value
Color	-	-	Black
specific gravity	g/cm ³	ISO 1183	1.33
Tensile strength	MPa	ISO	260
Tensile Elongation		527-1,2	>2
Flexural strength	MPa	ISO 178	360
Flexural modulus			17200
Charpy impact strength(notched)	kJ/m ²	ISO 179/1eA	7
Heat Deflection Temperature (1.8MPa)	°C	ISO 75-1,2	300
Volume resistivity	Ω•cm	IEC 60093	1×10 ²
Surface resistivity	Ω		1×10 ²
Flammability		UL 94	HB
Mold shrinkage	%	50x70x3 mmt	0.2~0.6
MOLDING CONDITION			
	°C	Drying	100x 4Hrs
		Melt Temperature	290~320
		Mold Temperature	80~120
	%	Inject. Pressure	30~70
		Inject. Velocity	30~60

*All property values shown in this data sheet are the representative values and not minimum value of this material.

