



Titalon X600CF

樹脂 RESIN : PAMXD6 RESIN

產品說明 PRODUCT DESCRIPTION : 30%CF 填充、高剛性、低吸濕規格

項目 Properties	單位 Unit	測試方法 method	數值 Value
顏色 Color	-	-	Black
比重 specific gravity	g/cm ³	ISO 1183	1.36
拉伸強度 Tensile strength 拉伸率 Tensile Elongation	MPa	ISO 527-1,2	240 >1
彎曲強度 Flexural strength 彎曲模數 Flexural modulus	MPa	ISO 178	350 25000
衝擊強度(有缺口) Charpy impact strength(notched)	kJ/m ²	ISO 179/1eA	5
熱變形溫度(1.8MPa) Heat Deflection Temperature(1.8MPa)	°C	ISO 75-1,2	230
體積阻抗 Volume resistivity 表面阻抗 Surface resistivity	Ω•cm Ω	IEC 60093	10 ⁻²⁻⁴ 10 ⁻²⁻⁴
耐燃性 Flammability		UL 94	HB
模收縮 Mold shrinkage	%	50x70x3 mmt	0.1~0.4
成型條件 MOLDING CONDITION	°C	乾燥條件 Drying	100x 4Hrs
		料管溫度 Melt Temp.	240~270
		模具溫度 Mold Temp.	100~130
	%	射出壓力 Inject. Press.	50~70
射出速度 Inject. Velocity		50~70	

*以上數值為材料的代表性測試值、並非該規格材料的最低值。

*All property values shown in this data sheet are the representative values and not minimum value of this material.

