



Titalon XB00GF

樹脂 RESIN : PAMXD6 RESIN

產品說明 PRODUCT DESCRIPTION : 60%GF 填充、高剛性、低吸濕、低收縮

項目 Properties		單位 Unit	測試方法 method	數值 Value
顏色 Color		-	-	Natural
比重 specific gravity		g/cm ³	ISO 1183	1.75
拉伸強度 Tensile strength 拉伸率 Tensile Elongation		MPa	ISO 527-1,2	265 >2
彎曲強度 Flexural strength 彎曲模數 Flexural modulus		MPa	ISO 178	405 22000
衝擊強度(有缺口) Charpy impact strength(notched)		kJ/m ²	ISO 179/1eA	12
熱變形溫度(1.8MPa) Heat Deflection Temperature(1.8MPa)		℃	ISO 75-1,2	230
體積阻抗 Volume resistivity 表面阻抗 Surface resistivity		Ω•cm Ω	IEC 60093	1×10 ¹⁴ 1×10 ¹⁴
耐燃性 Flammability			UL 94	HB
模收縮 Mold shrinkage		%	50x70x3 mmt	0.1~0.4
成型條件 MOLDING CONDITION	℃	乾燥條件 Drying		100x 4Hrs
		料管溫度 Melt Temp.		240~270
		模具溫度 Mold Temp.		100~130
	%	射出壓力 Inject. Press.		50~70
射出速度 Inject. Velocity		50~70		

*以上數值為材料的代表性測試值、並非該規格材料的最低值。

*All property values shown in this data sheet are the representative values and not minimum value of this material.

