TRIESA

BESTDUR®

PXG6 /01

TECHNICAL DATA SHEET

PET natural lubrified with 30% glass fibre reinforcement and V-0 quality.

		STANDARD	UNIT	DRY	CONDITIONED
GENERALS	Density	ISO 1183	gr/cm³	1,70	
	Melt Flow Index	ISO 1133	gr/10 min.	-	
	Humidity Pelets	ISO 1110	%	0,2	
	Hardness	SHORE D	Points	80	
	Mold Shrinkage	-	%	-	

		STANDARD	UNIT	DRY	CONDITIONED
MECHANICAL	Tensile Strenght	ISO 527	N/mm²	130	
	Elogantion at break	ISO 527	%	2	
	Tensile Modulus	ISO 527	N/mm²	9500	
	Charpy Impact	23 °C ISO 179	Kj/m²	45	
		-40 °C ISO 179	Kj/m²	-	
	Charpy Impact	23 °C ISO 179	Kj/m²	7	
		-40 °C ISO 179	Kj/m²	-	

		STANDARD	UNIT	DRY	CONDITIONED
ELECTRICAL	Surface Resistivity	IEC 93	Ohm	10^14	
	Dielectric strength	IEC 243	Kv/mm	-	
	Tracking lindex (C.T.I.)	IEC 112	Kv/mm	250	

		STANDARD	UNIT	DRY	CONDITIONED
THERMAL	Deflection Temp. Under Load	0,4 N ISO 75/A	°C	240	
	(H.D.T.)	1,8 N ISO 75/A	°C	215	
	VICAT Temperatura	ISO 306	°C	-	

- The values provided in this data sheet correspond to our knowledge. All products must be subjected to in company test by the user before application.
- These datas do not release you from the obligation to test our products as to their suitability for the intended processes and final use.
- These data may not valid such material used in combination with any other materials or additives or in- any process.
- Triesa assumes no liability and makes no warranties of any kind, expressed or implied how to use this information data.
- UL measurements are done in our lab according to this norm.

[HongKong] +852-69575415 [China GuangDong] +135-3858-6433 [China ShangHai] +188-1699-6168

		STANDARD	UNIT	DRY	CONDITIONED
OTHERS	UL - Flammability	UL-94	-	V-0	
	Glow Wire	IEC 695	°C	960	
	Fammability speed	FMV 302	mm/min.	-	
	Ashes	Triesa Test	%	~30	
	Water absorption (24h)	ISO 62	%	-	
	Flame Retardant			YES	

		RECOMMENDED VALUES
PROCESSING	Drying Material	3h - 4h 120°C
	Mold. Temperature	80°C-100°C
	Processing Temperature	260°C-280°C
	Back Temperature	250°C-255°C
	Middle Temperature	260°C-270°C
	Nozzle Temperature	275°C-280°C
	Hold Pressure	70 - 100 Mpa

- The values provided in this data sheet correspond to our knowledge. All products must be subjected to in company test by the user before application.
-These datas do not release you from the obligation to test our products as to their suitability for the intended processes and final use.
- These data may not valid such material used in combination with any other materials or additives or in- any process.
- Triesa assumes no liability and makes no warranties of any kind, expressed or implied how to use this information data.
- UL measurements are done in our lab according to this norm.

TECHNICAL DATA SHEET

[HongKong] +852-69575415 [China GuangDong] +135-3858-6433 [China ShangHai] +188-1699-6168