TRIESA

BESTNYL ECO ®

SI35VI02BHR

TECHNICAL DATA SHEET

Polyamide 6 black lubrified with 35% glass fibre reinforcement and heat stabilized. Is a compounding with high quality recyled PA 6, for sectors looking for quality materials with ecofriend environment.

		STANDARD	UNIT	DRY	CONDITIONED
GENERALS	Density	ISO 1183	gr/cm³	1,41	
	Melt Flow Index	ISO 1133	gr/10 min.	-	
	Humidity Pelets	ISO 1110	%	0,2	
	Hardness	SHORE D	Points	79	
	Mold Shrinkage	-	%	-	

		STANDARD	UNIT	DRY	CONDITIONED
MECHANICAL	Tensile Strenght	ISO 527	N/mm²	150	-
	Elogantion at break	ISO 527	%	3	-
	Tensile Modulus	ISO 527	N/mm²	8900	-
	Charpy Impact	23 °C ISO 179	Kj/m²	65	-
		-40 °C ISO 179	Kj/m²	-	-
	Charpy notched Impact	23 °C ISO 179	Kj/m²	10	-
		-40 °C ISO 179	Kj/m²	-	-

		STANDARD	UNIT	DRY	CONDITIONED
ELECTRICAL	Surface Resistivity	IEC 93	Ohm	10^13	
	Dielectric strength	IEC 243	Kv/mm	40	
	Tracking lindex (C.T.I.)	IEC 112	Kv/mm	-	

		STANDARD	UNIT	DRY	CONDITIONED
THERMAL	Deflection Temp. Under Load	0,4 N ISO 75/A	°C	210	
	(H.D.T.)	1,8 N ISO 75/A	°C	200	
	VICAT Temperatura	ISO 306	°C	>200	

- The values provided in this data sheet correspond to our knowledge. All products must be subjected to in company test by the user before application.
-These datas do not release you from the obligation to test our products as to their suitability for the intended processes and final use.
- These data may not valid such material used in combination with any other materials or additives or in- any process.
- Triesa assumes no liability and makes no warranties of any kind, expressed or implied how to use this information data.
- UL measurements are done in our lab according to this norm.

[HongKong] +852-69575415 [China GuangDong] +135-3858-6433 [China ShangHai] +188-1699-6168

		STANDARD	UNIT	DRY	CONDITIONED
OTHERS	UL - Flammability	UL-94	-	HB	
	Glow Wire	IEC 695	°C	-	
	Fammability speed	FMV 302	mm/min.	<100	
	Ashes	Triesa Test	%	35	
	Water absorption (24h)	ISO 62	%	-	
	Heat Stabilized			YES	

		RECOMMENDED VALUES
PROCESSING	Drying Material	2h - 4h 110°C-120°C
	Mold. Temperature	60°C-90°C
	Processing Temperature	240°C-255°C
	Back Temperature	235°C-245°C
	Middle Temperature	245°C-255°C
	Nozzle Temperature	250°C-260°C
	Hold Pressure	70 - 110 Mpa

- The values provided in this data sheet correspond to our knowledge. All products must be subjected to in company test by the user before application.
-These datas do not release you from the obligation to test our products as to their suitability for the intended processes and final use.
- These data may not valid such material used in combination with any other materials or additives or in- any process.
- Triesa assumes no liability and makes no warranties of any kind, expressed or implied how to use this information data.
- UL measurements are done in our lab according to this norm.

TECHNICAL DATA SHEET

[HongKong] +852-69575415 [China GuangDong] +135-3858-6433 [China ShangHai] +188-1699-6168