

DENILEN B 4010 CB WT

PP resin, 40% glass fiber reinforced, heat stabilized for injection moulding



PROPERTY	CONDITIONS	NORMS	UNITS	VALUE
PHYSICAL PROPERTIES				
Density	-	ISO-1183	g/cm ³	1,21
MVR (230°C/2,16 kg)	-	ISO-1133	cm ³ /10 min	2,5
Linear Mould Shrinkage	-	ASTM D-955	%	0,3
Trasversal Mould Shrinkage	-	ASTM D-955	%	0,7
Water Adsorption	23°C-24h	ASTM D-570	%	0,02
THERMAL PROPERTIES				
Vicat Softening Point	VICAT B (50 N)	ASTM D-1525	°C	145
Heat Distortion Temperature	HDT A (1,80 MPa)	ASTM D-648	°C	150
Long Term Temperature	-	Internal Method	°C	120
MECHANICAL PROPERTIES				
Impact Strength Izod Notched	23 °C	ISO-180/A	kJ/m ²	10
Impact Strength Izod Unnotched	23 °C	ISO-180/U	kJ/m ²	40
Tensile Strength at Break	23 °C	ISO-527/1-2	MPa	90
Elongation at Break	23 °C	ISO-527/1-2	%	2
Tensile Modulus	23 °C	ISO-527/1-2	MPa	8000
ELECTRICAL PROPERTIES				
Comparative Tracking Index	-	IEC 60112	V	600

DENILEN B 4010 CB WT

PP resin, 40% glass fiber reinforced, heat stabilized for injection moulding



FLAME RESISTANCE

Thickness 3,0 mm	-	UL 94	-	HB
Thickness 1,5 mm	-	UL 94	-	HB
GWFI (1 mm)	-	IEC 60695-2-12	°C / mm	650
GWFI (2 mm)	-	IEC 60695-2-12	°C / mm	650
GWIT (1 mm)	-	IEC 60695-2-13	°C / mm	675
GWIT (2 mm)	-	IEC 60695-2-13	°C / mm	675