

DENYL A

PA/ABS blend unfilled for injection moulding



PROPERTY	CONDITIONS	NORMS	UNITS	VALUE
PHYSICAL PROPERTIES				
Density	-	ISO-1183	g/cm ³	1,06
Linear Mould Shrinkage	-	ASTM D-955	%	1,3
Trasversal Mould Shrinkage	-	ASTM D-955	%	1,3
Water Adsorption	23°C-24h	ASTM D-570	%	1
THERMAL PROPERTIES				
Vicat Softening Point	VICAT B (50 N)	ASTM D-1525	°C	105
Heat Distortion Temperature	HDT A (1,80 MPa)	ASTM D-648	°C	60
Long Term Temperature	-	Internal Method	°C	80
MECHANICAL PROPERTIES				
Impact Strength Izod Notched	23 °C	ISO-180/A	kJ/m ²	20
Impact Strength Izod Unnotched	23 °C	ISO-180/U	kJ/m ²	NB
Tensile Strength at Break	23 °C	ISO-527/1-2	MPa	40
Elongation at Break	23 °C	ISO-527/1-2	%	>100
Tensile Modulus	23 °C	ISO-527/1-2	MPa	1800